



impexmetal s.a.
ALUMINIUM KONIN

62-510 KONIN ul.Hutnicza 1

Tel. (063) 247 44 22

(063) 247 44 88

Fax. (063) 247 47 89

INSPECTION CERTIFICATE No 433234/05 Date: 2015-04-02
EN 10204/3.1

ORDER No	P031448
-----------------	----------------

GOODS DESCRIPTION			
Alloy	Batch No	Dimensions [mm]	Temper
EN-AW 5754	433234/05	Thickness	2,000
		Width	1500,00
		Length	3000,00
			H22


CHEMICAL ANALYSIS [%]									
Heat/Melt No	Fe	Si	Cu	Mg	Mn	Cr	Ti	Zn	Other
530492	0,343	0,244	0,050	2,812	0,330	0,084	0,026	0,035	

MECHANICAL AND OTHER PROPERTIES					
Slab/Coil No	Rm	R _{p0,2}	A ₅₀	Hardness	Other
	[MPa]	[MPa]	[%]	[HB, V]	
53049211	231	166	20	-	-

Tolerance of dimensions and the shape - positive result

WE HEREBY CERTIFY THAT THE GOODS COMPLY WITH YOUR ORDER AND NORM:

EN485-1,2,4; EN573-3; EN15088


CENTRAL LABORATORY
Laboratory Foreperson
Waldemar Dobry

TRANSPORT and STORAGE CONDITIONS OF ALUMINIUM STRIPS AND SHEETS BY CUSTOMER

Strips (sheets) should be transported by covered, dry and clean means of transport preserving current regulation, protecting it from mechanical damage, humidity and harmful environmental factors.

Strips (sheets) should be stored in covered, dry and clean rooms protecting them from humidity and action of active chemicals. Protection of coil edges against mechanical damage should be taken into special attention. Butting face damage can cause difficulties in uncoiling process.

The storage temperature room should be stable. Changes of the temperature in stock cause that air moisture is condensed on the strip surface, in consequence of capillary activity, between coils, penetrates inside and inducing corrosion.

Disregard of above mentioned transport and storage conditions absolves supplier from responsibilities for material quality.