

Tilaja Purchaser  
TIBNOR OY  
NIINISTÖNKATU 7  
05800 HYVINKÄÄ FINLAND  
Tilaus nro Order No.  
4501395738

Tilausvahvistus Order Confirmation  
76479

Vastaanottaja Consignee  
TIBNOR OY  
NIINISTÖNKATU 7  
05800 HYVINKÄÄ FINLAND  
Asiakkaan merkki Shipping mark

Päivämäärä Date  
11.01.2023  
Valmistajan merkki  
Mark of the Manufacturer



Todistus Certificate  
31

Laatumerkintä Quality Marking  
S355K2 N S355J2 N

Tarkastajan leima  
Stamp of Inspector

*Mxx*

Toimitustyyppi Delivery type  
REST DELIVERY

Sulatus nro levy nro Cast No. Plate No.  
XXXXX XXX XX XX

Vastaanottajan leima  
Stamp of Surveyor

Muut leimaukset  
Other Stamps

Tuote Product  
CUT LENGTHS  
Laji Grade  
MULTISTEEL/S355K2+N EN 10025-2:2019  
Laatuselvitys Quality Specifications  
STRUCTURAL STEEL,MEETS REQ. OF EN 10025-2 S355K2/J2

Toleranssit Tolerances  
EN 10051:2010

Tekniset vaatimukset ja/tai viralliset määräykset Technical terms of Delivery and/or Official Regulations

Positio Item	Mitat mm Dimensions mm	Merkki Marke	Kpl Pcs	Paino kg Weight kg	Sulatus levy nro Cast plate No	SP nro SP No	UT	MT	Turvamerkki Safetymark
<b>HOT ROLLED STEEL IN BUNDLES CUT LENGTHS MILL EDGES</b>									
<b>FLANGEABILITY (C) ACC. TO STEEL GRADE SPEC.;CEV MAX 0,43%,MEETS REQ.OF EN10025-2 S355J0</b>									
010	10.00 X 1500 X	3000	4501395738	A005.A02182	STD				
			7	2480	26654	010	010		
010	10.00 X 1500 X	3000							
			36	12745	26656	058	058		
			***	43	15225				

### Raah Steel Works

Täten todistamme, että toimitus on tilausvahvistuksen mukainen.  
We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Testaus ja tarkastus Testing and Inspection

*Minna Valkama*

### MINNA VALKAMA

Valtuutettu tarkastaja Authorized inspection representative

Yhtiön nimi Company Name: SSAB Europe Oy  
Kotipaikka Registered Office: HÄMEENLINNA


Osoite Address: PL 93, P.O Box 93  
FI-92101 RAAHE, FINLAND

Puhelin Telephone: 020 5911  
+358 20 5911

Y-tunnus Business ID: 2389445-7

Tilaja Purchaser  
TIBNOR OY  
NIINISTÖNKATU 7  
05800 HYVINKÄÄ FINLAND  
Tilaus nro Order No.  
4501395738

Vastaanottaja Consignee  
TIBNOR OY  
NIINISTÖNKATU 7  
05800 HYVINKÄÄ FINLAND  
Asiakkaan merkki Shipping mark

Päivämäärä Date  
**11.01.2023** AMH  
Valmistajan merkki  
Mark of the Manufacturer 

Tilauksen vahvistus Order Confirmation  
**76479**

Laji Grade  
MULTISTEEL/S355K2+N

Lisävaatimukset Additional requirements

Jatkuvavalettua happiterästä  
Oxygen steel, continuous casting

Laatuseelvitys Quality Specifications

Fully killed, Fine grain practiced

STRUCTURAL STEEL, MEETS REQ. OF EN 10025-2 S355K2/J2

Pos. Item	Sulatus, k. erä nro Cast. test No	T-tila Cond	Vetokoe Tensile test														Taivutuskoe Bend test		Huom Nb	Päästö Tempering °C															
			K2	°C	RP02 MPa	RT05 MPa	REL MPa	REH MPa	RM MPa			A %			RE / RM	RM * A5	RAZ %				Keskiarvo Average	K5	D = X t												
010	26654	010	NR	31						406	525																								
010	26656	058	NR	31						412	526																								

K2: 31=CENTRE, TRANSVERSE  
NR=NORMALIZING ROLLING

Pos. Item	Sulatus k. erä nro Cast. test No	Iskukoe Impact test						FA %			LE (mm)			*Specimen Unbroken			Erikoiskokeet Special tests			Huom Nb	Päästö Tempering °C															
		K3	°C	1	2	3	Keskiarvo Average	W (mm)	1	2	3	Keskiarvo Average	1	2	3	Keskiarvo Average	K4	°C	1			2	Keskiarvo Average													
010	26654	010	135	-020	100	100	116																													
010	26656	058	135	-020	110	104	102																													

FA = Sitkeämurtuman osuus Shear fracture appearance  
LE = Poikittainen laajenema Lateral Expansion

K3: 135=CH-V/ISO-V(J), 7.5X10,CENTRE,LONGIT,KV600

### Raah Steel Works

Testaus ja tarkastus Testing and Inspection



#### MINNA VALKAMA

Valtuutettu tarkastaja Authorized inspection representative

Yhtiön nimi Company Name: SSAB Europe Oy  
Kotipaikka Registered Office: HÄMEENLINNA

Osioite Address: PL 93, P.O Box 93  
FI-92101 RAAHE, FINLAND

Puhelin Telephone: 020 5911  
+358 20 5911

Y-tunnus Business ID: 2389445-7

Täten todistamme, että toimitus on tilausvahvistuksen mukainen.

We hereby certify that the material described above has been tested and complies with the terms of the order confirmation.

Sulatus nro Cast No Schmelzen Nr. No de coulén	Koe nro Test No Prüf Nr. Essai No	Positio Item Pos. Poste	Cekv Ceq Caq Cég Cekv	Analyysi % Chemical composition % Chemisch Zusammensetzung % Composition Chimique % (*=ppm)												Päivämäärä Date Datum Date		
				C	SI	MN	P	S	AL	NB	V	CU	CR	NI	MO	11.01.2023	AMH	
26654		010	.40	.146	.19	1.40	.011	.008	.031	.017	.010	.023	0.06	0.05	.005			
26656		010	.40	.148	.20	1.40	.009	.006	.036	.017	.009	.018	0.05	0.05	.004			

CEQ=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15

### Raah Steel Works

Testaus ja tarkastus    Testing and Inspection  
Prüfung und Kontrolle    Essais et Contrôle

SSAB Europe Oy, Raah Steel Works testing laboratories T002 and T010 are accredited by the FINAS accreditation service, accreditation requirement SFS-EN ISO/IEC 17025.

Steel manufactured and supplied by Raah Steel Works is free from radiation.

#### MINNA VALKAMA

Valtuutettu tarkastaja    Authorized inspection representative  
Sachverständiger    Inspector autorisé

Yhtiön nimi Company Name:    SSAB Europe Oy  
Kotipaikka Registered Office:    HÄMEENLINNA

Osoite Address:    PL 93, P.O Box 93  
FI-92101 RAAHE, FINLAND

Puhelin Telephone:    020 5911  
+358 20 5911

Y-tunnus Business ID:    2389445-7

**Declaration of performance**  
(according to EU No 305/2011 and 574/2014)

DoP id. S011\_02

Hot rolled strip product S355K2 / 1.0596  
according to  
EN 10025-2:2019  
for bolted, welded and riveted structures.

SSAB  
P.O Box 70  
101 20 Stockholm  
SWEDEN  
T: +46 8 45 45 700  
Email: info@ssab.com  
Website: ssab.com

TÜV NORD Systems GmbH & Co. KG  
Grosse Bahnstrasse 31  
D-22525 Hamburg  
Germany  
T: +49 40 8557 2368

Assessment system and verification for constancy  
of performance  
**System 2+**

The performance of the product identified in this document is  
in conformity with the set of declared performance. This declaration of performance  
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,  
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala  
Vice President, hot rolled plate and strip products,  
SSAB Europe Oy, Raahе Steelworks  
Raahе 2015-06-09



05

0045-CPR-0573  
EN 10025-1:2004

Dop id: S011_02 EN 10025-2:2019		Performance				Harmonized technical specification	
S355K2	Thickness	Tolerances for nominal width w				EN 10025-1:2004	
Tolerances on dimensions and shapes.	Nominal thickness (mm)	w ≤ 1200	1200 < w ≤ 1500	1500 < w ≤ 1800	w > 1800		
							t ≤ 2,00
	Thickness	2,00 < t ≤ 2,50	± 0,21	± 0,24	± 0,26		± 0,29
		2,50 < t ≤ 3,00	± 0,23	± 0,25	± 0,28		± 0,30
		3,00 < t ≤ 4,00	± 0,25	± 0,28	± 0,30		± 0,31
		4,00 < t ≤ 5,00	± 0,28	± 0,30	± 0,32		± 0,33
		5,00 < t ≤ 6,00	± 0,30	± 0,32	± 0,33		± 0,36
		6,00 < t ≤ 8,00	± 0,33	± 0,35	± 0,36		± 0,40
		8,00 < t ≤ 10,00	± 0,37	± 0,38	± 0,39		± 0,46
		10,00 < t ≤ 12,50	± 0,40	± 0,41	± 0,43		± 0,49
		12,50 < t ≤ 15,00	± 0,43	± 0,44	± 0,46		± 0,53
		15,00 < t ≤ 25,00	± 0,46	± 0,48	± 0,52		± 0,58
Width	Nominal width	Tolerances					
		Mill edges		Trimmed edges*			
	w	Lower	Upper	Lower	Upper		
	w ≤ 1 200	0	+20	0	+3		
	1 200 < w ≤ 1 850	0	+20	0	+5		
	w > 1 850	0	+25	0	+6		
* Tolerances for trimmed edges apply to products with nominal thickness t ≤ 10 mm; for nominal thickness t > 10 mm the upper tolerances shall be agreed at the time of enquiry and order.							
Length	Nominal length	Tolerances					
		Lower		Upper			
	l < 2 000	0		+10			
	2 000 ≤ l < 8 000	0		+0,005 x l			
l ≥ 8 000	0		+40				
Flatness	Nominal thickness	Tolerances					
		w ≤ 1 200	1 200 < w ≤ 1 500	w > 1500			
	t ≤ 25,00	18	23	28			

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	≤ 16	355	
	> 16 ≤ 25	345	
Tensile strength	thickness mm	min (Mpa)	max (Mpa)
	< 3	510	680
	≥ 3 ≤ 25	470	630
Elongation	thickness mm	min %	
	> 1.5 ≤ 2	14	
	> 2 ≤ 2.5	15	
	> 2.5 < 3	16	
	≥ 3 ≤ 25	20	
Impact strength	thickness mm	temperature, °C	min. energy, J
	≤ 25	-20	40
Weldability CEV	thickness mm	CEV max %	
	≤ 25	0.45	
Durability (chemical composition)	element	max %	
	C	0.20	
	Si	0.55	
	Mn	1.60	
	P	0.025	
	S	0.025	
	N		
	Cu	0.55	
	Ni	0.42	
	Cr	0.29	
Mo	0.11		

**Declaration of performance**  
(according to UK CPR 2020 No 1359)

DoP id. S011\_02

Hot rolled strip product S355K2 / 1.0596  
according to  
EN 10025-2:2019  
for bolted, welded and riveted structures.

SSAB  
P.O Box 70  
101 20 Stockholm  
SWEDEN  
T: +46 8 45 45 700  
Email: info@ssab.com  
Website: ssab.com

LRQA Verification Limited (Reg. No. 4929226)  
Registered office  
1 Trinity Park, Bickenhill Lane  
Birmingham  
B37 7ESA

Assessment system and verification for constancy  
of performance  
**System 2+**

The performance of the product identified in this document is  
in conformity with the set of declared performance. This declaration of performance  
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,  
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala  
Vice President, hot rolled plate and strip products,  
SSAB Europe Oy, Raahe Steelworks  
Raahe 2015-06-09



05

0038/CPR/PRJ11100341405/ 01

EN 10025-1:2004

Dop id: S011_02 EN 10025-2:2019		Performance				Harmonized technical specification	
S355K2	Thickness	Tolerances for nominal width w				EN 10025-1:2004	
Tolerances on dimensions and shapes.	Nominal thickness (mm)	w ≤ 1200	1200 < w ≤ 1500	1500 < w ≤ 1800	w > 1800		
							t ≤ 2,00
	Thickness	2,00 < t ≤ 2,50	± 0,21	± 0,24	± 0,26		± 0,29
		2,50 < t ≤ 3,00	± 0,23	± 0,25	± 0,28		± 0,30
		3,00 < t ≤ 4,00	± 0,25	± 0,28	± 0,30		± 0,31
		4,00 < t ≤ 5,00	± 0,28	± 0,30	± 0,32		± 0,33
		5,00 < t ≤ 6,00	± 0,30	± 0,32	± 0,33		± 0,36
		6,00 < t ≤ 8,00	± 0,33	± 0,35	± 0,36		± 0,40
		8,00 < t ≤ 10,00	± 0,37	± 0,38	± 0,39		± 0,46
		10,00 < t ≤ 12,50	± 0,40	± 0,41	± 0,43		± 0,49
		12,50 < t ≤ 15,00	± 0,43	± 0,44	± 0,46		± 0,53
		15,00 < t ≤ 25,00	± 0,46	± 0,48	± 0,52		± 0,58
Width	Nominal width	Tolerances					
		Mill edges		Trimmed edges*			
	w	Lower	Upper	Lower	Upper		
	w ≤ 1 200	0	+20	0	+3		
	1 200 < w ≤ 1 850	0	+20	0	+5		
	w > 1 850	0	+25	0	+6		
* Tolerances for trimmed edges apply to products with nominal thickness t ≤ 10 mm; for nominal thickness t > 10 mm the upper tolerances shall be agreed at the time of enquiry and order.							
Length	Nominal length	Tolerances					
		Lower		Upper			
	l < 2 000	0		+10			
	2 000 ≤ l < 8 000	0		+0,005 x l			
l ≥ 8 000	0		+40				
Flatness	Nominal thickness	Tolerances					
		w ≤ 1 200	1 200 < w ≤ 1 500	w > 1500			
	t ≤ 25,00	18	23	28			

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	≤ 16	355	
	> 16 ≤ 25	345	
Tensile strength	thickness mm	min (Mpa)	max (Mpa)
	< 3	510	680
	≥ 3 ≤ 25	470	630
Elongation	thickness mm	min %	
	> 1.5 ≤ 2	14	
	> 2 ≤ 2.5	15	
	> 2.5 < 3	16	
	≥ 3 ≤ 25	20	
Impact strength	thickness mm	temperature, °C	min. energy, J
	≤ 25	-20	40
Weldability CEV	thickness mm	CEV max %	
	≤ 25	0.45	
Durability (chemical composition)	element	max %	
	C	0.20	
	Si	0.55	
	Mn	1.60	
	P	0.025	
	S	0.025	
	N		
	Cu	0.55	
	Ni	0.42	
	Cr	0.29	
Mo	0.11		

**Declaration of performance**  
(according to EU No 305/2011 and 574/2014)

DoP id. S010\_02

Hot rolled strip product S355J2 / 1.0577  
according to  
EN 10025-2:2019  
for bolted, welded and riveted structures.

SSAB  
P.O Box 70  
101 20 Stockholm  
SWEDEN  
T: +46 8 45 45 700  
Email: info@ssab.com  
Website: ssab.com

TÜV NORD Systems GmbH & Co. KG  
Grosse Bahnstrasse 31  
D-22525 Hamburg  
Germany  
T: +49 40 8557 2368

Assessment system and verification for constancy  
of performance  
**System 2+**

The performance of the product identified in this document is  
in conformity with the set of declared performance. This declaration of performance  
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,  
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala  
Vice President, hot rolled plate and strip products,  
SSAB Europe Oy, Raahе Steelworks  
Raahе 2015-06-09



05

0045-CPR-0573  
EN 10025-1:2004



Dop id: S010_02 EN 10025-2:2019		Performance				Harmonized technical specification	
S355J2	Thickness	Tolerances for nominal width w				EN 10025-1:2004	
Tolerances on dimensions and shapes.	Nominal thickness (mm)	w ≤ 1200	1200 < w ≤ 1500	1500 < w ≤ 1800	w > 1800		
							t ≤ 2,00
	Thickness	2,00 < t ≤ 2,50	± 0,21	± 0,24	± 0,26		± 0,29
		2,50 < t ≤ 3,00	± 0,23	± 0,25	± 0,28		± 0,30
		3,00 < t ≤ 4,00	± 0,25	± 0,28	± 0,30		± 0,31
		4,00 < t ≤ 5,00	± 0,28	± 0,30	± 0,32		± 0,33
		5,00 < t ≤ 6,00	± 0,30	± 0,32	± 0,33		± 0,36
		6,00 < t ≤ 8,00	± 0,33	± 0,35	± 0,36		± 0,40
		8,00 < t ≤ 10,00	± 0,37	± 0,38	± 0,39		± 0,46
		10,00 < t ≤ 12,50	± 0,40	± 0,41	± 0,43		± 0,49
		12,50 < t ≤ 15,00	± 0,43	± 0,44	± 0,46		± 0,53
		15,00 < t ≤ 25,00	± 0,46	± 0,48	± 0,52		± 0,58
Width	Nominal width	Tolerances					
		Mill edges		Trimmed edges*			
	w	Lower	Upper	Lower	Upper		
	w ≤ 1 200	0	+20	0	+3		
	1 200 < w ≤ 1 850	0	+20	0	+5		
	w > 1 850	0	+25	0	+6		
* Tolerances for trimmed edges apply to products with nominal thickness t ≤ 10 mm; for nominal thickness t > 10 mm the upper tolerances shall be agreed at the time of enquiry and order.							
Length	Nominal length	Tolerances					
		Lower		Upper			
	l < 2 000	0		+10			
	2 000 ≤ l < 8 000	0		+0,005 x l			
l ≥ 8 000	0		+40				
Flatness	Nominal thickness	Tolerances					
		w ≤ 1 200	1 200 < w ≤ 1 500	w > 1500			
	t ≤ 25,00	18	23	28			

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	≤ 16	355	
	> 16 ≤ 25	345	
Tensile strength	thickness mm	min (Mpa)	max (Mpa)
	< 3	510	680
	≥ 3 ≤ 25	470	630
Elongation	thickness mm	min %	
	> 1.5 ≤ 2	14	
	> 2 ≤ 2.5	15	
	> 2.5 < 3	16	
	≥ 3 ≤ 25	20	
Impact strength	thickness mm	temperature, °C	min. energy, J
	≤ 25	-20	27
Weldability CEV	thickness mm	CEV max %	
	≤ 25	0.45	
Durability (chemical composition)	element	max %	
	C	0.20	
	Si	0.55	
	Mn	1.60	
	P	0.025	
	S	0.025	
	N		
	Cu	0.55	
	Ni	0.42	
	Cr	0.29	
Mo	0.11		

**Declaration of performance**  
(according to UK CPR 2020 No 1359)

DoP id. S010\_02

Hot rolled strip product S355J2 / 1.0577  
according to  
EN 10025-2:2019  
for bolted, welded and riveted structures.

SSAB  
P.O Box 70  
101 20 Stockholm  
SWEDEN  
T: +46 8 45 45 700  
Email: info@ssab.com  
Website: ssab.com

LRQA Verification Limited (Reg. No. 4929226)  
Registered office  
1 Trinity Park, Bickenhill Lane  
Birmingham  
B37 7ESA

Assessment system and verification for constancy  
of performance  
**System 2+**

The performance of the product identified in this document is  
in conformity with the set of declared performance. This declaration of performance  
is issued in accordance with Regulations (EU) No 305/2011 and 574/2014,  
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:



Jarkko Matkala  
Vice President, hot rolled plate and strip products,  
SSAB Europe Oy, Raahe Steelworks  
Raahe 2015-06-09



05

0038/CPR/PRJ11100341405/ 01

EN 10025-1:2004

Dop id: S010_02 EN 10025-2:2019		Performance				Harmonized technical specification	
S355J2	Thickness	Tolerances for nominal width w				EN 10025-1:2004	
Tolerances on dimensions and shapes.	Nominal thickness (mm)	w ≤ 1200	1200 < w ≤ 1500	1500 < w ≤ 1800	w > 1800		
							t ≤ 2,00
	Thickness	2,00 < t ≤ 2,50	± 0,21	± 0,24	± 0,26		± 0,29
		2,50 < t ≤ 3,00	± 0,23	± 0,25	± 0,28		± 0,30
		3,00 < t ≤ 4,00	± 0,25	± 0,28	± 0,30		± 0,31
		4,00 < t ≤ 5,00	± 0,28	± 0,30	± 0,32		± 0,33
		5,00 < t ≤ 6,00	± 0,30	± 0,32	± 0,33		± 0,36
		6,00 < t ≤ 8,00	± 0,33	± 0,35	± 0,36		± 0,40
		8,00 < t ≤ 10,00	± 0,37	± 0,38	± 0,39		± 0,46
		10,00 < t ≤ 12,50	± 0,40	± 0,41	± 0,43		± 0,49
		12,50 < t ≤ 15,00	± 0,43	± 0,44	± 0,46		± 0,53
		15,00 < t ≤ 25,00	± 0,46	± 0,48	± 0,52		± 0,58
Width	Nominal width	Tolerances					
		Mill edges		Trimmed edges*			
	w	Lower	Upper	Lower	Upper		
	w ≤ 1 200	0	+20	0	+3		
	1 200 < w ≤ 1 850	0	+20	0	+5		
	w > 1 850	0	+25	0	+6		
* Tolerances for trimmed edges apply to products with nominal thickness t ≤ 10 mm; for nominal thickness t > 10 mm the upper tolerances shall be agreed at the time of enquiry and order.							
Length	Nominal length	Tolerances					
		Lower		Upper			
	l < 2 000	0		+10			
	2 000 ≤ l < 8 000	0		+0,005 x l			
l ≥ 8 000	0		+40				
Flatness	Nominal thickness	Tolerances					
		w ≤ 1 200	1 200 < w ≤ 1 500	w > 1500			
	t ≤ 25,00	18	23	28			

Yield strength	thickness mm	min (Mpa)	max (Mpa)
	≤ 16	355	
	> 16 ≤ 25	345	
Tensile strength	thickness mm	min (Mpa)	max (Mpa)
	< 3	510	680
	≥ 3 ≤ 25	470	630
Elongation	thickness mm	min %	
	> 1.5 ≤ 2	14	
	> 2 ≤ 2.5	15	
	> 2.5 < 3	16	
	≥ 3 ≤ 25	20	
Impact strength	thickness mm	temperature, °C	min. energy, J
	≤ 25	-20	27
Weldability CEV	thickness mm	CEV max %	
	≤ 25	0.45	
Durability (chemical composition)	element	max %	
	C	0.20	
	Si	0.55	
	Mn	1.60	
	P	0.025	
	S	0.025	
	N		
	Cu	0.55	
	Ni	0.42	
	Cr	0.29	
Mo	0.11		