


A01 Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteel.eu.com	A03 Doc nr. 2023001925 00		A04 
	A02 Inspection certificate 3.1, EN10204.		
	A07, A09 Reference 5500001625 NAANTALI 11014456 4500067032/00010	A08 Order nr. 57949 A	
A06 Customer/Consignee SERVICE CENTRE MAASTRICHT B.V. B. U. FELJEN POSTBUS 10.000 1970 CA IJMUIDEN NOORDHOLLAND	B01,B02,B03,B04,B15 Hot rolled dry, Coil, S355MC, YMPRESS WG S:01-2010. Mill edges. Impact test. Suitable for: Part galvanising, Cutting into sheet. Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.22/-0.22 mm). PRODUCE AND TEST ACCORDING TO EN 10149-2		C70 STEEL MAKING PROCESS: BO
	B09,B10,B11 Dimensions 1500 mm X 15.00 mm		
	B13 Total Mass KG 32200	B08 Total NR. 1	
	A11 Dispatch Note 30883	A10 Transport ESPERANZA	

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant'

C50

PROD-IDENT: 3188551

MASS KG: 32200

NR: 1

CAST NR: H7497

B07,B08,B13

TENSILE TEST

C10-29

C01	C01/C02	C10	C03 Temp (°C)	C11 Rp0.2 (MPa)	C12 Rm (MPa)	C13 A (%)	C16 Rp0.2/Rm (%)
Bottom Middle	Surface Longitudinal	Prismatical	+20	386	506	30.0	76

IMPACT TEST AND OTHER TESTS

C40,C60,C65

C01	C01/C02	C10	C03 Temp °C	B05	C41 mm	C40,C60,C65	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean
Bottom Middle	Surface Longitudinal	Prismatical	-20	0	10.1	ISO-V	J	203	186	239	209

CHEMICAL COMPOSITION in %

B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb
H7497	0.057	1.308	0.015	0.005	0.009	0.035	0.007	0.017	0.016	0.003	0.035
CAST NR.	C82 v	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al_ZO	C88 C-eq1	B99 Country of Melt and Pour			
H7497	0.003	.0038	.0000	0.001	0.002	0.034	.281	Netherlands			

C-eq1: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV

Jeffrey Flemming
General Manager

IJmuiden, 9 January 2023

