


A01

ArcelorMittal Belgium NV
ArcelorMittal Gent
 John Kennedylaan, 51
 9042 Gent (België)
 Tel: +32 9.347.31.11
 Fax: +32 9.347.49.07

A02
 CERTIFICATE
 TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.

A03
 190818893 P. 01/02

A04
 2455186

A05
 AUTHOR OF THE DOCUMENT
 AM GENT/ QUALITY DEPARTMENT

A06.1 CUSTOMER
 OY KONTINO AB
 HAKINTIE, 6 - P027
 FIN-01301 VANTAA
 FINLAND
 3445176

A06.2 DESTINATION
 OY KONTINO AB
 HAKINTIE, 6 - P027
 FIN-01301 VANTAA
 FINLAND
 344517

A07 YOUR ORDER NO 1112371
A08 ORDER NUMBER 98176
A09 DISPATCH NOTE 2455186
A10 DATE 19-04-2019
A11 ORDER NUMBER 98176
A12 DATE

A13 YOUR ORDER NO 1112371
A14 DATE 02-11-2018
A15 CONTRACT NO FC91KON001
A16 YOUR REFERENCES
A17 OUR REFERENCES OBC-IN/SOEL
 STANDARD = AM FCE

B01-B04 MATERIAL - COLD ROLLED STEEL SHEETS, ANNEALED, SKINPASSED, QUALITY DC02

B09 ITEM B13 LENGTH B10 WIDTH B11 THICKNESS REF. CUSTOMER
 O2 3.000 1.500 2.00 CRL208

CHEMICAL ANALYSIS
 C70 STEELMAKING PROCESS: LD

B09 ITEM	B08 NUMBER	B13 GROSS WEIGHT	B07 COIL NO	B08 CAST N.	C	Mn	Si	P	S	N	Al	Ti	Cr	Ni	Cu	Nb	B	V	Mo
		KG			10 ⁻³ %	10 ⁻² %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %
02	878583049	33	2344	23073809	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
	878583051	33	2342	23073892	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
	878583052	32	2270	23073953	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
	878583053	32	2272	23073984	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
	878583054	32	2270	23074039	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
	878583056	32	2272	23074138	69	32	7	12	7	38	51	1	25	17	10	0	1	0	2
		194																	
		6																	
		194																	
		13770																	


B09 ITEM B13 GROSS WEIGHT
 6 194 13770

MECHANICAL PROPERTIES
 TENSILE TEST

B09 ITEM	PACK NR	C04	C02	C11	C12	C13
		YIELD STRENGTH	YIELD STRENGTH	YIELD STRENGTH	YIELD STRENGTH	YIELD STRENGTH
		Rp0.2	Rm	Rm	Rm	A
		MPa	MPa	MPa	MPa	%
02	878583049	F	D	225	338	40
	878583051	F	D	225	338	40
	878583052	F	D	225	338	40
	878583053	F	D	225	338	40
	878583054	F	D	225	338	40
	878583056	F	D	225	338	40
		6				

C04 CONDITION OF THE SPECIMEN
 V: AGED F: NON-AGED N: NORMALISED
C02 DIRECTION SPECIMEN
 L: OGR S: 45GR D: 90GR

Zetel: Keizerinlaan 66, B-1000 Brussel (België) BTW BE 0400.106.281 RPR Brussel

A01  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	A02 CERTIFICATE TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 190818893 P. 02/02	A09 DISPATCH NOTE 2455186 19-04-2019	A06.1 CUSTOMER OY KONTINO AB HAKINTIE, 6 - P027 FIN-01301 VANTAA FINLAND 3445176
A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT		A08 ORDER NUMBER 98176 A07 YOUR ORDER NO 1112371 DATE 02-11-2018 CONTRACT NO FC91KON001 YOUR REFERENCES OUR REFERENCES OBC-IN/SOEL		A06.2 DESTINATION OY KONTINO AB HAKINTIE, 6 - P027 FIN-01301 VANTAA FINLAND 344517
B01-B04 MATERIAL - COLD ROLLED STEEL SHEETS, ANNEALED, SKINPASSED, QUALITY DCO2 STANDARD = AM FCE				
REMARKS TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM. REFERENCES CRL208 CO4 CONDITION OF THE SPECIMEN CO2 DIRECTION SPECIMEN V:AGED F:NON-AGED N:NORMALISED L:OGR S:45GR D:90GR Zetel: Keizerinlaan 66, B-1000 Brussel (België) BTW BE 0400.106.291 RPR Brussel R. SLOCK QUALITY DEPARTMENT GENT 19-04-2019 Z01				