


AO1  <b>ArcelorMittal</b>  <b>ArcelorMittal Belgium NV</b> <b>ArcelorMittal Gent</b>  John Kennedylaan, 51 9042 Gent (België)  Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	AO2 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	AO3 190770513 P. 01/01	AO9 DISPATCH NOTE 2443328 DATE 12-04-2019	AO6.1 CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	AO5 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	AO8 ORDER NUMBER 06381 DATE	AO7 YOUR ORDER NO 12639 DATE 21-03-2019	AO6.2 DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 050183
		CONTRACT NO FC92HTMO08	YOUR REFERENCES	
		OUR REFERENCES OBC-IN/SOEL		


BO1-BO4 MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED, STANDARD = EN 10130:2006  
 (00-12-2006)  
 QUALITY DCO1

BO9 ITEM	B10 WIDTH MM	B11 THICKNESS MM	REF. CUSTOMER
02	1.500	2.00	DCO1

BO9 ITEM	PACK NR	B13 GROSS WEIGHT KG	BO7 COIL NO	BO8 CAST N.	CHEMICAL ANALYSIS C70 STEELMAKING PROCESS: LD															MECHANICAL PROPERTIES TENSILE TEST				
					C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	CO4	CO2	C11	C12	C13
					C	Mn	Si	P	S	N	Al_t	Ti	Cr	Ni	Cu	Nb	B	V	Mo			YIELD Rp0.2 MPa	STRENGTH Rm MPa	A %
02	865273801 865273806 2	12400 12320 24720	24323637 24323644	49662 49662	38	21	6	17	16	33	37	1	30	20	20	0	1	0	2	F	D	187	317	41
					38	21	6	17	16	33	37	1	30	20	20	0	1	0	2	F	D	187	317	41
	2	24720																						

REMARKS  
 -----  
 TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.  
 REFERENCES  
 -----  
 DCO1

GENT 12-04-2019

R. SLOCK  
 QUALITY DEPARTMENT  
  
 Z01

CO4 CONDITION OF THE SPECIMEN V: AGED F: NON-AGED N: NORMALISED	CO2 DIRECTION SPECIMEN L: OGR S: 45GR D: 9OGR
--	--