


A01  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	A02 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 192131333 P. 01/01	A09 DISPATCH NOTE 2843434 DATE 15-11-2019	A06.1 CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	A08 ORDER NUMBER 55050 DATE	A07 YOUR ORDER NO 13257 DATE 01-10-2019	A06.2 DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 050183
		CONTRACT NO FC94HTMO01	YOUR REFERENCES	
		OUR REFERENCES OBC-AU/DHAH		

BO1-BO4 SEE BELOW

BO9 ITEM	B10 WIDTH MM	B11 THICKNESS MM	REF. CUSTOMER
04	1.070	1,00	DCO1
08	1.500	1,00	DCO1
14	1.500	2,00	DCO1

BO9 ITEM	PACK NR	B13 GROSS WEIGHT KG	BO7 COIL NO	BO8 CAST N.	CHEMICAL ANALYSIS C70 STEELMAKING PROCESS: LD															MECHANICAL PROPERTIES TENSILE TEST				
					C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	CO4	CO2	C11	C12	C13
					C	Mn	Si	P	S	N	Al	Ti	Cr	Ni	Cu	Nb	B	V	Mo			YIELD Rp0.2 MPa	STRENGTH Rm MPa	A %
04	865690742 1	9700 9700	31720478	59252	45	21	10	13	11	34	32	1	29	17	25	0	1	0	2	F	D	183	315	40
08	865681707 865681725 865681744 3	9310 8950 8750 27010	31439486 31439509 31439516	58970 58970 58970	49	21	10	15	14	26	35	1	35	19	28	0	1	0	3	F	D	203	331	38
14	865684315 1 5	6630 6630 43340	31478883	58863	41	20	5	7	12	27	27	1	29	22	33	0	1	0	3	F	D	165	295	43

BO1-BO4

- MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED,
 (00-12-2006)
 QUALITY DCO1
 - STAND: EN 10131 (2006) NORM.TOL.
 REMARKS


STANDARD = EN 10130:2006

TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.
 REFERENCES

DCO1

GENT 15-11-2019

R. SLOCK
 QUALITY DEPARTMENT



Z01