

SSAB EMEA AB, SE-781 84 BORLÄNGE, Sweden

<b>Inspection certificate</b> EN 10 204 - 3.1	A02	<b>Issuing department</b> Quality inspection	A05	<b>Purchaser order no</b> st#27570_O761	A07	<b>Our order no</b> 803534-5	A08	<b>Invoice no</b> 2596551	A19	<b>Certificate no and date</b> 14883529 2014-06-12	A03
--	-----	---	-----	--	-----	---------------------------------	-----	------------------------------	-----	---	-----

<b>Purchaser</b> ALUSTEEL OY AB TELAKKATIE 4 FI-23500 UUSIKAUPUNKI FINLAND	A11	<b>Product</b> HR pickled wide strip in coils	B01	<b>Marking</b> Manufacturer, MATERIAL ID	B06	<b>Standard/rules</b> EN 10149-2	B02			
	24574	<b>Quantity</b> 1	B08	<b>Dimensions [mm]</b> T 12 W 1500 L 0	B09-B11	<b>Weight [kg]</b> 23760	B12	<b>Deliv. Cond.</b> B04	<b>Internal code</b> B16	
		<b>Consignee</b> ALUSTEEL OY AB TELAKKATIE 4 FI-23500 UUSIKAUPUNKI FINLAND	A06	<b>Customer marks</b>	B15					
<b>MATERIAL ID</b> 60-8632-563788										B07

Chemical composition										C71-C92	Carbon equivalent etc	C93-C99						
<b>Heat no</b> 60-8632	<b>C</b> .065	<b>Si</b> .02	<b>Mn</b> .60	<b>P</b> .006	<b>S</b> .003	<b>Cr</b> .04	<b>Ni</b> .05	<b>Mo</b> .02	<b>V</b> .01	<b>Ti</b> .00	<b>Cu</b> .01	<b>Al</b> .040	<b>Nb</b> .037	<b>B</b> .0002	<b>N</b> .005	<b>Cekv</b> .18	Cekv = C + Mn/6 + (Ni + Cu)/15 + (Cr + Mo + V)/5	

Testtype	Millcode	Specimen position	Direction	Treatment	Specimen type	Temp [degr C]	Test results				
Tensile test	BCH461	Top end	Longitudinal	Delivery condition	Rectangular 380x40		C11 Reh [MPa] 395	C12 Rm [MPa] 476	C13 A5 [%] 33,0		
Impact test	BCH462	Top end	Longitudinal	Delivery condition	Charpy-V 10x10	-20	C42 E [J] 304	C42 E [J] 256	C42 E [J] 304	C43 Ave [J] 288	
Bend test	BCH463	Top end	Transvers	Delivery condition	Rectangular 300x25		C50 The test is satisfactory				

Production time: 2014-06-04

It is hereby certified that the material described above complies with the requirements of the order.	Z02	This certificate is produced with EDP and valid without signature	Z01	A22	A04
		Material Testing/ L Smedh/ M Eriksson/ L Söderqvist			