

A01 Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteeleurope.com	A03 Doc nr. 2022007831 00	A04 TATA STEEL
	A02 Inspection certificate 3.1, EN10204.	
A06 Customer/Consignee SERVICE CENTRE MAASTRICHT B.V. B.U. FEIJEN POSTBUS 10.000 1970 CA IJMUIDEN NOORDHOLLAND	A07, A09 Reference 4500054127 NAANTALI 11014486 00040	A08 Order nr. 59076 D
	B01,B02,B03,B04,B15 Hot rolled pickled, Coil, S650MC, YMPRESS WG S:01-2010. 1.00 G/M2/Side oiled. Mill edges. Suitable for: Cutting into sheet. Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.18/-0.18 mm). PRODUCE AND TEST ACCORDING TO EN 10149-2 Country of Melt and Pour : Netherlands	
		C70 STEEL MAKING PROCESS: BO
		B09,B10,B11 Dimensions 1500 mm X 5 mm
		B13 Total Mass KG 31120
		B08 Total NR. 1
		A11 Dispatch Note 20744
		A10 Transport VALENCIA

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant'

C50

PROD-IDENT: 612360

MASS KG: 31120

NR: 1

CAST NR: W7788

B07,B08,B13

TENSILE TEST

C10-29

C01	C01/C02	C10	C03	C11	C12	C13	C16
Bottom Middle	Surface Longitudinal	Prismatical	Temp (°C)	Rp0.2 (MPa)	Rm (MPa)	A (%)	Rp0.2/Rm (%)
			+20	700	806	18.0	87

CHEMICAL COMPOSITION in %


B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb
W7788	0.061	1.870	0.011	0.002	0.050	0.029	0.009	0.031	0.023	0.005	0.069
CAST NR.	C82 V	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al_ZO	C88 C-eql				
W7788	0.009	.0051	.0000	0.105	0.002	0.028	.384				

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV

Jeffrey Flemming
General Manager



IJmuiden, 24 January 2022