

AO1  ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	AO2 CERTIFICATE ----- INSPECTION CERTIFICATE ACCORDING EN10204-3.1 OR EQUIVALENT.	AO3 231807303 P. 01/02	AO9 DISPATCH NOTE 4684420 DATE 08-12-2023	AO6.1 CUSTOMER FEON OY TEOLLISUUSKATU 33 FIN-00510 HELSINKI FINLAND 1038076 AO6.2 DESTINATION FEON OY HEPOKARINTIE 9 FIN-23500 UUSIKAUPUNKI FINLAND 0074098	
	AO5 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	AO8 ORDER NUMBER 96450 DATE	AO7 YOUR ORDER NO 48666 DATE 04-09-2023		CONTRACT NO GH34FEH001
		YOUR REFERENCES			OUR REFERENCES OBC-AU/DHAH

BO1-BO4 MATERIAL - HOT ROLLED STEEL COILS ,PICKLED, QUALITY S355MC STAND: EN 10051 (2010) (FRAC: 1/2 TOLERANCE TO RESPECT (-))				STANDARD = EN 10149-2 (00-09-2013)			
--	--	--	--	------------------------------------	--	--	--

BO9 ITEM	BO10 WIDTH MM	BO11 THICKNESS MM	REF. CUSTOMER
O2	1.500	3,00	2463220
O4	1.500	4,00	2463260


		CHEMICAL ANALYSIS C70 STEELMAKING PROCESS: LD																		
BO9 ITEM	PACK NR	BO13 GROSS WEIGHT KG	BO7 COIL NO	BO8 CAST N.	C71 C	C72 Mn	C73 Si	C74 P	C75 S	C76 N	C77 Al_t	C78 Ti	C79 Cr	C80 Ni	C81 Cu	C82 Nb	C83 B	C84 V	C85 Mo	CEQ2
					10 ⁻³ %	10 ⁻² %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %
O2	867905792	21410	65005251	61279	62	33	10	16	7	28	21	1	20	10	20	27	0	2	0	123
	867905798	26720	65005749	61277	72	37	20	17	5	32	38	1	20	10	20	24	0	2	0	140
	867905803	26650	65005732	61265	62	36	20	15	7	36	39	1	20	10	30	28	0	2	0	129
	867905809	26630	65005763	61253	71	33	10	12	7	41	37	1	20	10	30	24	0	2	0	133
	867905814	26580	65005756	61269	66	35	20	20	5	38	30	1	20	10	20	26	0	2	0	131
	867905816	26700	65005787	61277	72	37	20	17	5	32	38	1	20	10	20	24	0	2	0	140
	867905822	26730	65005770	61250	72	34	20	14	7	37	33	1	20	10	20	27	0	2	0	135
7		181420																		
O4	867905301	26400	65005916	61335	64	54	20	13	4	13	34	1	10	10	20	24	0	2	0	158
	867905312	26590	65005862	61340	66	54	20	14	4	28	32	1	20	10	20	29	0	3	0	163
	867905316	26540	65005923	61333	66	53	10	16	5	28	42	1	10	0	40	28	0	2	0	159
	867907552	26610	65097489	61330	67	51	10	12	5	18	39	2	20	0	20	25	0	1	0	158
	867907559	26420	65097496	61333	66	53	10	16	5	28	42	1	10	0	40	28	0	2	0	159
	867907561	26520	65097502	61331	66	52	10	16	4	35	38	1	20	10	20	26	0	2	0	159
	867907566	26700	65097519	61332	75	54	20	15	5	18	39	2	20	10	20	24	0	2	0	171
	867907568	26580	65097526	61325	68	50	10	19	7	41	42	1	20	10	40	27	0	2	0	159
	867908266	26090	65098107	61335	64	54	20	13	4	13	34	1	10	10	20	24	0	2	0	158
	9		238450																	
16		419870																		

CO4 CONDITION OF THE SPECIMEN V:AGED F:NON-AGED N:NORMALISED	CO2 DIRECTION SPECIMEN L:OGR S:45GR D:9OGR
---	---

AO1  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	AO2 CERTIFICATE ----- INSPECTION CERTIFICATE ACCORDING EN10204-3.1 OR EQUIVALENT.	AO3 231807303 P. 02/02	AO9 DISPATCH NOTE 4684420 DATE 08-12-2023	AO6.1 CUSTOMER FEON OY TEOLLISUUSKATU 33 FIN-00510 HELSINKI FINLAND 1038076
	AO5 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	AO8 ORDER NUMBER 96450 DATE	AO6.2 DESTINATION FEON OY HEPOKARINTIE 9 FIN-23500 UUSIKAUPUNKI FINLAND 0074098	
		AO7 YOUR ORDER NO 48666 DATE 04-09-2023		
		CONTRACT NO GH34FEH001		
		YOUR REFERENCES		
	OUR REFERENCES OBC-AU/DHAH			

BO1-BO4 MATERIAL - HOT ROLLED STEEL COILS ,PICKLED, QUALITY S355MC STAND: EN 10051 (2010) (FRAC: 1/2 TOLERANCE TO RESPECT (-))	STANDARD = EN 10149-2 (00-09-2013)
---	------------------------------------

		MECHANICAL PROPERTIES					
		TENSILE TEST					
BO9 ITEM	PACK NR	CO4	CO2	C11 YIELD Rp0.2 MPa	C12 STRENGTH Rm MPa	C13 A %	
02	867905792	F	L	366	475	36	
	867905798	F	L	360	475	37	
	867905803	F	L	371	477	35	
	867905809	F	L	375	476	37	
	867905814	F	L	370	481	37	
	867905816	F	L	369	481	35	
	867905822	F	L	371	479	35	
7							
04	867905301	F	L	365	472	35	
	867905312	F	L	381	491	34	
	867905316	F	L	373	484	38	
	867907552	F	L	378	484	34	
	867907559	F	L	374	490	34	
	867907561	F	L	375	480	34	
	867907566	F	L	378	489	33	
	867907568	F	L	376	486	34	
	867908266	F	L	371	473	35	
	9						

REMARKS ----- TENSILE TEST SPECIMEN LC/LO/BO 120/ 5.65 SQR(SO)/ 20 MM. REFERENCES ----- ORDER ITEM 02 - 2463220 ORDER ITEM 04 - 2463260	GENT 08-12-2023	R. SLOCK QUALITY DEPARTMENT  Z01				
<table border="1"> <tr> <td>CO4 CONDITION OF THE SPECIMEN</td> <td>CO2 DIRECTION SPECIMEN</td> </tr> <tr> <td>V: AGED F: NON-AGED N: NORMALISED</td> <td>L: OGR S: 45GR D: 9OGR</td> </tr> </table>	CO4 CONDITION OF THE SPECIMEN	CO2 DIRECTION SPECIMEN	V: AGED F: NON-AGED N: NORMALISED	L: OGR S: 45GR D: 9OGR		
CO4 CONDITION OF THE SPECIMEN	CO2 DIRECTION SPECIMEN					
V: AGED F: NON-AGED N: NORMALISED	L: OGR S: 45GR D: 9OGR					