

<b>A01</b> Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteeleurope.com	<b>A03 Doc nr.</b> 2022007822 00	<b>A04</b> <h1 style="text-align: center;">TATA STEEL</h1>
	<b>A02</b> Inspection certificate 3 1, EN10204.	
<b>A05 Customer/Consignee</b> SERVICE CENTRE MAASTRICHT B.V. B. U. FEIJEN POSTBUS 10.000 1970 CA IJMUIDEN NOORDHOLLAND	<b>A07, A09 Reference</b> 5500001424 NAANTALI 11014191 4500035592/00010	<b>A08 Order nr.</b> 57898 A
	<b>B01, B02, B03, B04, B15</b> Not rolled pickled, Coil, 6355ME, YMPRESS WG 8:01-2010. 1.00 G/M2/side oiled. Mill edges. Impact test. Suitable for: Part galvanising, Cutting into sheet. Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.19/-0.19 mm). PRODUCE AND TEST ACCORDING TO EN 10149-2 Country of Melt and Pour : Netherlands	
		<b>C70</b> STEEL MAKING PROCESS: BO
		<b>B09, B10, B11 Dimensions</b> 1500 mm X 10.00 mm
		<b>B13 Total Mass KG</b> 31160
		<b>B08 Total NR.</b> 1
		<b>A11 Dispatch Note</b> 20744
		<b>A10 Transport</b> VALENCIA

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant'

C50

PROD-IDENT: 612539	MASS RG: 31160	NR: 1	CAST NR: W8405	B07, B08, B13
TENSILE TEST				C10-29

C01	C01/C02	C10	C03 Temp (°C)	C11 R <sub>0.2</sub> (MPa)	C12 R <sub>m</sub> (MPa)	C13 A (%)	C16 R <sub>0.2</sub> /R <sub>m</sub> (%)
Bottom	Surface	Prismatical	+20	405	504	28.5	80
Middle	Longitudinal						

C01	C01/C02	C10	C03 Temp °C	B05	C41 mm	C40, C60, C65	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean
Bottom	Surface	Prismatical	-20	0	7.5	ISO-V	J	199	212	207	206
Middle	Longitudinal										

CHEMICAL COMPOSITION in %												
B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb	
W8405	0.075	1.000	0.015	0.004	0.009	0.032	0.022	0.029	0.020	0.003	0.025	
CAST NR.	C82 V	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al <sub>2O</sub>	C88 C-eq1					
W8405	0.002	0.0030	0.0000	0.001	0.004	0.030	0.251					

C-eq1: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756617



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756612



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756613



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756615

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV

Jeffrey Fleming  
General Manager

IJmuiden, 24 January 2022



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756607



Purchase Order:  
4500061749  
Vendor Batch:  
612539

130016170001756608