

A01 Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteeleurope.com	A03 Doc nr. 2022029648 00	A04 <h2 style="text-align: center;">TATA STEEL</h2>
	A02 Inspection certificate 3.1, EN10204, A07, A09 Reference 5500001401 NAANTALI 11014190 5500001080/00010	
A06 Customer/Consignee SERVICE CENTRE MAASTRICHT B.V. B.V. FLIJEN POSTBUS 10.000 1970 CA IJMUIDEN NOORDHOLLAND	B01, B02, B03, B04, B15 Hot rolled pickled, Coil, 2355MC, VMPRESS MG 9:01-2010, 1.00 G/M2/Side oiled. Mill edges. Impact test. Suitable for: Part galvanising, Cutting into sheet. Tolerance EN 10051 : 2010 (R) (Width tolerance +20/-0 mm) Dev.Tol. (thickness tolerance +0.18/-0.18 mm). PRODUCE AND TEST ACCORDING TO EN 10149-2 Country of Melt and Pour : Netherlands	C70 STEEL MAKING PROCESS: BO
		B09, B10, B11 Dimensions 1500 mm X 8.00 mm
		B13 Total Mass KG 48640
		A10 Transport CONFIDENT

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant' C50

PROD-IDENT: 613401 MASS KG: 24260 NR: 1 CAST NR: Z2203 B07, B08, B13

TENSILE TEST C10-29

C01	C01/C02	C10	C03 Temp (°C)	C11 ReH (MPa)	C12 Rm (MPa)	C13 A (%)	C16 ReH/Rm (%)
Bottom	Surface	Prismatical	+20	404	478	31.0	85
Middle	Longitudinal						

IMPACT TEST AND OTHER TESTS C40, C60, C65

C01	C01/C02	C10	C03 Temp °C	B05	C41 mm	C40, C60, C65	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean
Bottom	Surface	Prismatical	-20	0	5.0	ISO-V	J	117	117	108	114
Middle	Longitudinal										

PROD-IDENT: 613415 MASS KG: 24380 NR: 1 CAST NR: Z2203 B07, B08, B13

TENSILE TEST C10-29

C01	C01/C02	C10	C03 Temp (°C)	C11 ReH (MPa)	C12 Rm (MPa)	C13 A (%)	C16 ReH/Rm (%)
Bottom	Surface	Prismatical	+20	399	477	31.0	84
Middle	Longitudinal						

IMPACT TEST AND OTHER TESTS C40, C60, C65

C01	C01/C02	C10	C03 Temp °C	B05	C41 mm	C40, C60, C65	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean
Bottom	Surface	Prismatical	-20	0	5.0	ISO-V	J	99	108	107	105
Middle	Longitudinal										

CHEMICAL COMPOSITION in %

B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb
Z2203	0.065	1.008	0.015	0.005	0.008	0.033	0.008	0.019	0.015	0.002	0.022
CAST NR.	C82 V	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al_2O	C88 C-eql				
Z2203	0.003	.0033	.0000	0.001	0.002	0.031	.239				

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV Jeffrey Fleming General Manager IJmuiden, 23 March 2022	 <i>Jeffrey Fleming</i>	Purchase Order: 4500055892 Vendor Batch: 613415 130016160001760017		Purchase Order: 4500055892 Vendor Batch: 613415 130016160001760019
---	---	--	---	--

Page 1 of 1 201, 202