


A01 Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteel.eu.com	A03 Doc nr. 2022107438 00		A04 
	A02 Inspection certificate 3.1, EN10204.		
	A07, A09 Reference 5500001401 NAANTALI 11014190 5500001080/00010	A08 Order nr. 57737 A	
A06 Customer/Consignee SERVICE CENTRE MAASTRICHT B.V. B.U. FEIJEN POSTBUS 10.000 1970 CA IJMUIDEN NOORDHOLLAND	B01,B02,B03,B04,B15 Hot rolled pickled, Coil, S355MC, YMPRESS WG S:01-2010. 1.00 G/M2/Side oiled. Mill edges. Impact test. Suitable for: Part galvanising, Cutting into sheet. Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.18/-0.18 mm). PRODUCE AND TEST ACCORDING TO EN 10149-2		C70 STEEL MAKING PROCESS: BO
	B09,B10,B11 Dimensions 1500 mm X 8.00 mm		B13 Total Mass KG 24420
			B08 Total NR. 1
			A10 Transport VALENCIA

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant'

C50

PROD-IDENT: 616482 MASS KG: 24420 NR: 1 CAST NR: H4857 B07,B08,B13

TENSILE TEST C10-29

C01	C01/C02	C10	C03 Temp (°C)	C11 ReH (MPa)	C12 Rm (MPa)	C13 A (%)	C16 ReH/Rm (%)
Bottom Middle	Surface Longitudinal	Prismatical	+20	399	501	28.0	80

IMPACT TEST AND OTHER TESTS C40,C60,C65

C01	C01/C02	C10	C03 Temp °C	B05	C41 mm	C40,C60,C65	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean
Bottom Middle	Surface Longitudinal	Prismatical	-20	0	5.0	ISO-V	J	103	115	120	113

CHEMICAL COMPOSITION in %

B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb
H4857	0.074	0.995	0.014	0.001	0.019	0.029	0.013	0.023	0.018	0.004	0.025
CAST NR.	C82 v	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al_ZO	C88 C-eq1	B99 Country of Melt and Pour			
H4857	0.005	.0037	.0000	0.001	0.001	0.027	.248	Netherlands			

C-eq1: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV

Jeffrey Flemming
General Manager



IJmuiden, 24 November 2022