


<b>A01</b>  <b>ArcelorMittal</b>  <b>ArcelorMittal Belgium NV</b> <b>ArcelorMittal Gent</b>  John Kennedylaan, 51 9042 Gent (België)  Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	<b>A02</b> CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	<b>A03</b> 201077623 P. 01/01	<b>A09</b> DISPATCH NOTE 3221490 DATE 25-08-2020	<b>A06.1</b> CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	<b>A05</b> AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	<b>A08</b> ORDER NUMBER 85732 DATE	<b>A07</b> YOUR ORDER NO 14103 DATE 07-07-2020	<b>A06.2</b> DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 050183
		CONTRACT NO GCO3HTMO05	YOUR REFERENCES	
		OUR REFERENCES OBC-AU/DHAH		

BO1-BO4 SEE BELOW

BO9 ITEM	B10 WIDTH	B11 THICKNESS	REF. CUSTOMER
	MM	MM	
02	1.500	2.00	DCO1

CHEMICAL ANALYSIS																				MECHANICAL PROPERTIES				
C70 STEELMAKING PROCESS: LD																				TENSILE TEST				
BO9 ITEM	PACK NR	B13 GROSS WEIGHT	BO7 COIL NO	BO8 CAST N.	C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	CO4	CO2	C11 YIELD	C12 STRENGTH	C13
		KG			C	Mn	Si	P	S	N	Al <sub>t</sub>	Ti	Cr	Ni	Cu	Nb	B	V	Mo			Rp0.2	Rm	A
					10 <sup>-3</sup> %	10 <sup>-2</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-4</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %	10 <sup>-4</sup> %	10 <sup>-3</sup> %	10 <sup>-3</sup> %			MPa	MPa	%
02	866147631	9860	38856886	71018	44	21	6	15	12	32	31	1	28	27	26	0	1	2	4	F	D	201	332	40
	866147639	9440	38856893	71018	44	21	6	15	12	32	31	1	28	27	26	0	1	2	4	F	D	201	332	40
	866147642	7650	38856909	71018	44	21	6	15	12	32	31	1	28	27	26	0	1	2	4	F	D	201	332	40
	866148809	9360	38868256	71025	44	17	5	12	12	29	48	1	19	22	19	0	1	0	1	F	D	181	312	41
	866148830	9320	38868263	71025	44	17	5	12	12	29	48	1	19	22	19	0	1	0	1	F	D	181	312	41
	866148837	8900	38868270	71025	44	17	5	12	12	29	48	1	19	22	19	0	1	0	1	F	D	181	312	41
	6	54530																						
	6	54530																						

BO1-BO4

- MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED,  
 (OO-12-2006)  
 QUALITY DCO1  
 - STAND: EN 10131 (2006) NORM.TOL.  
 REMARKS


STANDARD = EN 10130:2006

TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.  
 REFERENCES

DCO1

GENT 25-08-2020

R. SLOCK  
 QUALITY DEPARTMENT



Z01