A01
Tata Steel IJmuiden BV
Wenckebachstraat 1
1951 JZ Velsen Noord
Postbus 10000
1970 CA IJmuiden The Netherlands
Telephone: 0251-492110

Company Trade Register 34040531
E-mail : info.testing@tatasteel.com

A07.A09 Reference
4500002642
11001464 00010

A05 Doc. nr
2017130660 00

A02
Inspection certificate 3.1, EN10204.

B01.B02.B03.B04.B15
Hot rolled pickled, Coil, S355MC, YMPRESS WG S:01-2010.
1.00 G/M2/Side oiled.
Mill edges.

Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.13/-0.13 mm).

TATA STEEL

Z04

A06 Customer/Consignee
NAANTALI STEEL SERVICE CENTRE OY
RAUTAKATU 5

21110 NAANTALI

FINLAND

A08 Order nr.
50199 A

A11 Dispatch note
66896

A10 Transport
JOLYN

B09.B10.B11 Dimensions
1500 mm X 3.00 mm

C10-C29 TENSILE TEST | HARDNESS | C40.C60.C65 IMPACT TEST AND OTHER TESTS

B07 PROD.-IDENT	B15 MASS kg	B08 NR	B07 CAST NR.		C01 -	C01/C02	C10	B05	C03 Temp °C	C11 R_{eH} MPa	C11 R_{eL} MPa	C11 R_p MPa	C12 R_m MPa	C15 A %	C15 A %	C16 R_{eH}/R_m %	C17 r-value	C18 n-value	C52	C01/C02	C10	B05	C41 mm	C40.C60.C65	C03 Temp °C	C44	C42 ind.	C42 ind.	C42 ind.	C45 mean	C95 ASTM E-112
741891	10500	1	H7501		32	1L	P		+ 20	397			483	32.5		82														
741892	10500	1	"																											
741893	10500	1	"																											
741974	10510	1	"		32	1L	P		+ 20	403			482	31.5		84														
741975	10520	1	"																											
741976	10360	1	"																											
TOTAL	62890	6																												

C71-C92 CHEMICAL COMPOSITION in %

B07 CAST NR.	B07 PROD.-IDENT	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb	C82 V	C83 N	C84 B	C85 C-eq	C86 Al-ZO	C87 Sn	C88 Ti	C89 C-eql
H7501		.072	0.505	.012	.006	0.006	0.040	.010	0.019	0.015	.001	.026	.001	.0022	.0001		0.038	.001	.001	.162

C44 1: J/cm² 2: J 3: Later. exp. (mm) 4: Contraction (%) 5: Shear area (%)

C01 1:1=Top 2:1=Edge 2=Middle 2=Middle 3=Bottom

C01 C02 1=Surface 2=Centre 3=¼ Surface L=Longitudinal T=Transverse Z=in Thickn dir D=in Diagonal dir

C10 P=prismatical C=cylindrical

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

C70 STEELMAKING PROCESS: BO

Z05 Stamp of the expert :

Z02
Tata Steel IJmuiden BV

SIMON BRAAM
MANAGER TESTING

IJMUIDEN, 5 DECEMBER 2017

Z05 | B06 | A04

Z01 We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions