A01
Tata Steel IJmuiden BV
Wenckebachstraat 1
1951 JZ Velsen Noord
Postbus 10000
1970 CA IJmuiden The Netherlands
Telephone: 0251-492110

Company Trade Register 34040551
E-mail: info.testing@tatasteeleurope.com

A07.A09 Reference
4500029651 SEVERAL
11001464 STEELCOMP 00020

A02
Inspection certificate 3.1, EN10204.

B01.B02.B05.B04.B15
Hot rolled pickled, Coil, S355MC, YMPRESS WG S:01-2010.
1.00 G/M2/Side oiled.
Mill edges.

Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.13/-0.13 mm).
PRODUCE AND TEST ACCORDING TO EN 10149-2

TATA STEEL

Z04

A05 Doc. nr
2020085033 00

A06 Customer/Consignee
NAANTALI STEEL SERVICE CENTRE OY
RAUTAKATU 5

21110 NAANTALI

FINLAND

A08 Order nr.
52910 B

A11 Dispatch note
38026

A10 Transport
EGON W

B09.B10.B11 Dimensions
1500 mm X 3.00 mm

C10-C29 TENSILE TEST

HARD-NESS

C40.C60.C65 IMPACT TEST AND OTHER TESTS

B07 PROD.-IDENT	B13 MASS kg	B08 NR	B07 CAST NR.		C01	C01/C02	C10	B05	C03 Temp °C	C11 R_{eH} MPa	C11 R_{eL} MPa	C11 $R_{p0.2}$ MPa	C12 R_m MPa	C13 A %	C15 A %	C16 R_{eH}/R_m %	C17 r-value	C18 n-value	C52	C01/C02	C10	B05	C41 mm	C40.C60.C65	C03 Temp °C	C44	C42 ind.	C42 ind.	C42 ind.	C43 mean	C95 ASTM E-112
782122	14038	1	R0836		32	1L	P		+ 20	395			489	34.5		81														
782123A	7773	1	"																											
782016	14098	1	"		32	1L	P		+ 20	399			485	34.5		82														
782018	13878	1	"																											
784030	10660	1	R3573		32	1L	P		+ 20	414			491	34.5		84														
784031	10660	1	"																											
784032	10640	1	"																											
TOTAL	81747	7																												

C71-C92 CHEMICAL COMPOSITION in %

B07 CAST NR.	B07 PROD.-IDENT	C71 C	C72 Mn	C75 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb	C82 V	C83 N	C84 B	C85 C-eq	C86 Al-ZO	C87 Sn	C88 Ti	C89 C-eql
R0836		.074	0.498	.015	.008	0.008	0.031	.017	0.026	0.022	.002	.025	.002	.0034	.0000		0.029	.005	.001	.166
R3573		.076	0.505	.017	.006	0.014	0.035	.008	0.022	0.018	.001	.025	.003	.0023	.0000		0.034	.001	.001	.167

C44 1: J/cm² 2: J 3: Later. exp. (mm) 4: Contraction (%) 5: Shear area (%)

C01 1:1=Top 2:1=Edge 2=Middle 2=Middle 3=Bottom

C01 C02 L=Longitudinal T=Transverse Z=in Thickn dir D=in Diagonal dir 1=Surface 2=Centre 3=¼ Surface

C10 P=prismatical C=cylindrical

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

C70 STEELMAKING PROCESS: BO

C50 Buigproef/Bend test/Biegeversuch/Test de flexion : goed/good/gut/concluant

Z05 Stamp of the expert :

Z02
Tata Steel IJmuiden BV

JEFFREY FLEMMING
MGR. MECH. TESTING

Jeffrey Flemming

IJMUIDEN, 24 SEPTEMBER 2020

Z05 B06 A04

Z01 We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions