A01
Tata Steel IJmuiden BV
Wenckebachstraat 1
1951 JZ Velsen Noord
Postbus 10000
1970 CA IJmuiden The Netherlands
Telephone: 0251-492110

Company Trade Register 34040531
E-mail: info.testing@tatasteeleurope.com

A07.A09 Reference
4500031885
11001473 00030

A02
Inspection certificate 3.1, EN10204.

B01.B02.B03.B04.B15
Hot rolled pickled, Coil, S355MC, YMPRESS WG S:01-2010.
1.00 G/M2/Side oiled.
Mill edges.
Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.14/-0.14 mm).
PRODUCE AND TEST ACCORDING TO EN 10149-2
Country of melt and pour : The Netherlands.

A05 Doc. nr
2021000201 00

Z04

A06 Customer/Consignee
NAANTALI STEEL SERVICE CENTRE OY
RAUTAKATU 5

21110 NAANTALI

FINLAND

A08 Order nr.
54701 C

A11 Dispatch note
65834

A10 Transport
OSTBORG

B09.B10.B11 Dimensions
1500 mm X 4 mm

C10-C29 TENSILE TEST

B07 PROD.-IDENT	B13 MASS kg	B08 NR	B07 CAST NR.		C01	C01/C02	C10	B05	C03 Temp °C	C11 R_{eH} MPa	C11 R_{eL} MPa	C11 $R_{p0.2}$ MPa	C12 R_m MPa	C15 A %	C15 A %	C16 R_{eH}/R_m %	C17 r-value	C18 n-value
806180	10560	1	R8237		32	1L	P		+ 20	396			479	34.0		83		
806181	10551	1	"															
806182A	8203	1	"															
806207	10580	1	R8246		32	1L	P		+ 20	401			484	35.0		83		
806208	10580	1	"															
806209	10441	1	"															
TOTAL	60915	6																

HARD-NESS

C40.C60.C65 IMPACT TEST AND OTHER TESTS

C52	C01/C02	C10	B05	C41 mm	C40.C60.C65	C05 Temp °C	C44	C42 ind.	C42 ind.	C42 ind.	C45 mean	C95 ASTM E-112

C71-C92 CHEMICAL COMPOSITION in %

B07 CAST NR.	B07 PROD.-IDENT	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb	C82 V	C83 N	C84 B	C85 C-eq	C86 Al-ZO	C87 Sn	C88 Ti	C89 C-eql
R8237		.071	0.505	.016	.007	0.013	0.029	.007	0.025	0.020	.002	.025	.003	.0031	.0000		0.028	.001	.001	.163
R8246		.072	0.520	.014	.006	0.014	0.031	.007	0.023	0.020	.002	.026	.002	.0025	.0001		0.031	.001	.002	.166

C44 1: J/cm² 2: J 3: Later. exp. (mm) 4: Contraction (%) 5: Shear area (%)

C01 1:1=Top 2:1=Edge 2=Middle 3=Bottom 2=Middle

C01 C02 L=Longitudinal 1=Surface T=Transverse 2=Centre Z=in Thickn dir 3=¼ Surface D=in Diagonal dir

C10 P=prismatical C=cylindrical

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

C70 STEELMAKING PROCESS: BO

C50 Buigproef/Bend test/Biegeversuch/Test de flexion : goed/good/gut/concluant

Z05

B06

A04

Z01 We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions

Z05 Stamp of the expert :

Z02
Tata Steel IJmuiden BV

JEFFREY FLEMMING
MGR. MECH. TESTING

IJMUIDEN, 2 JANUARI 2021