

A01 Tata Steel IJmuiden BV Wenckebachstraat 1 1951 JZ Velsen Noord Postbus 10000 1970 CA IJmuiden The Netherlands Telephone: 0251-492110 Company Trade Register 34040331 E-mail: info.testing@tatasteelurope.com	A03 Doc nr. 2021050271 00		A04 TATA STEEL
	A02 Inspection certificate 3.1, EN10204.		
	A07, A09 Reference 4500040232 11001475 00010	A08 Order nr. 51059 A	
A06 Customer/Consignee NAANTALI STEEL SERVICE CENTRE OY RAUTAKATU 5 21110 NAANTALI FINLAND	B01,B02,B03,B04,B15 Hot rolled pickled, Coil, S355MC, YMPRESS WG S:01-2010. 1.00 G/M2/Side oiled. Mill edges. Tolerance EN 10051 : 2010 (E) (Width tolerance +20/-0 mm) Dev.Tol. (Thickness tolerance +0.15/-0.15 mm). Country of Melt and Pour : Netherlands		C70 STEEL MAKING PROCESS: BO
	B09,B10,B11 Dimensions 1500 mm X 5 mm		
	B13 Total Mass KG 20722	B06 Total NR. 2	
	A11 Dispatch Note 23226	A10 Transport ROBIJN	

Buigproef/Bend test/Biegeversuch/Test de flexion : 'goed/good/gut/concluant' C50

PROD-IDENT: 840807	MASS KG: 10351	NR: 1	CAST NR: S5219	B07,B08,B13			
TENSILE TEST				C10-29			
C01	C01/C02	C10	C03	C11	C12	C13	C16
			Temp (°C)	ReH (MPa)	Rm (MPa)	A (%)	ReH/Rm (%)
Bottom Middle	Surface Longitudinal	Prismatical	+20	404	482	33.0	84

PROD-IDENT: 840806	MASS KG: 10371	NR: 1	CAST NR: S5219	B07,B08,B13			
TENSILE TEST				C10-29			
C01	C01/C02	C10	C03	C11	C12	C13	C16
			Temp (°C)	ReH (MPa)	Rm (MPa)	A (%)	ReH/Rm (%)
Bottom Middle	Surface Longitudinal	Prismatical	+20	404	482	33.0	84

CHEMICAL COMPOSITION in %											
B07 CAST NR.	C71 C	C72 Mn	C73 P	C74 S	C75 Si	C76 Al	C77 Cu	C78 Cr	C79 Ni	C80 Mo	C81 Nb
S5219	0.063	0.472	0.014	0.004	0.014	0.032	0.022	0.039	0.034	0.007	0.027
CAST NR.	C82 V	C83 N	C84 B	C85 Ti	C86 Sn	C87 Al_ZO	C88 C-eql				
S5219	0.003	0.0022	0.0000	0.001	0.004	0.030	0.155				

C-eql: C + Mn/6 + (Cr + Mo + V)/5 + (Ni + Cu)/15

We hereby confirm that we comply to the terms of our order acknowledgement and any agreed concessions.

Tata Steel IJmuiden BV

Jeffrey Flemming
Manager Mechanical Testing
IJmuiden, 1 May 2021

Jeffrey Flemming

Page 1 of 1 201,202