


A01  <b>ArcelorMittal</b>  <b>ArcelorMittal Belgium NV</b> <b>ArcelorMittal Gent</b>  John Kennedylaan, 51 9042 Gent (België)  Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	A02 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 190741433 P. 01/01	A09 DISPATCH NOTE 2435760 DATE 09-04-2019	A06.1 CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	A08 ORDER NUMBER 74244 DATE	A07 YOUR ORDER NO 12524 DATE 13-02-2019	A06.2 DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 050183
		CONTRACT NO FC92HTMOO2	YOUR REFERENCES	
		OUR REFERENCES OBC-IN/SOEL		

B01-B04 MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED, STANDARD = EN 10130:2006  
 (00-12-2006)  
 QUALITY DCO1

B09 ITEM	B10 WIDTH MM	B11 THICKNESS MM	REF. CUSTOMER
O2	1.250	0,50	DCO1
O4	1.250	0,75	DCO1

B09 ITEM	PACK NR	B13 GROSS WEIGHT KG	B07 COIL NO	B08 CAST N.	CHEMICAL ANALYSIS C70 STEELMAKING PROCESS: LD															MECHANICAL PROPERTIES TENSILE TEST				
					C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	C04	C02	C11	C12	C13
					C	Mn	Si	P	S	N	Al <sub>t</sub>	Ti	Cr	Ni	Cu	Nb	B	V	Mo			YIELD Rp0.2 MPa	STRENGTH Rm MPa	A %
O2	865232866	9300	23571918	718092	35	24	7	5	5	49	34	1	44	26	18	1	1	2	3	F	D	176	307	43
	865232879	9000	23571925	718092	35	24	7	5	5	49	34	1	44	26	18	1	1	2	3	F	D	176	307	43
	2	18300																						
O4	865261684	12000	24025096	48599	6	11	5	6	8	24	46	50	23	19	23	0	3	0	2	F	D	184	319	41
	865262003	11640	24025454	48599	6	11	5	6	8	24	46	50	23	19	23	0	3	0	2	F	D	161	316	39
	2	23640																						
	4	41940																						

REMARKS  
 -----  
 TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.  
 REFERENCES  
 -----  
 DCO1

GENT 09-04-2019

R. SLOCK  
 QUALITY DEPARTMENT



CO4 CONDITION OF THE SPECIMEN V: AGED F: NON-AGED N: NORMALISED	CO2 DIRECTION SPECIMEN L: OGR S: 45GR D: 9OGR
--	--

Z01