


A01  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	A02 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 191140043 P. 01/01	A09 DISPATCH NOTE 2547440 DATE 07-06-2019	A06.1 CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	A08 ORDER NUMBER 41246 DATE	A07 YOUR ORDER NO 12756 DATE 30-04-2019	A06.2 DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 050183
		CONTRACT NO FC93HTMOO1	YOUR REFERENCES	
		OUR REFERENCES OBC-IN/SOEL		

B01-B04 MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED, STANDARD = EN 10130:2006
 (00-12-2006)
 QUALITY DCO1

B09 ITEM	B10 WIDTH MM	B11 THICKNESS MM	REF. CUSTOMER
06	1.250	1,00	DCO1
12	1.500	2.00	DCO1


B09 ITEM	PACK NR	B13 GROSS WEIGHT KG	B07 COIL NO	B08 CAST N.	CHEMICAL ANALYSIS C70 STEELMAKING PROCESS: LD															MECHANICAL PROPERTIES TENSILE TEST				
					C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	C04	C02	C11	C12	C13
					C	Mn	Si	P	S	N	Al _t	Ti	Cr	Ni	Cu	Nb	B	V	Mo			YIELD Rp0.2 MPa	STRENGTH Rm MPa	A %
06	865370751	11330	25920659	51958	41	20	7	12	10	27	28	1	31	21	31	0	1	0	3	F	D	190	315	40
	865370758	11390	25920666	51958	41	20	7	12	10	27	28	1	31	21	31	0	1	0	3	F	D	190	315	40
	865370765	11480	25920673	51963	46	20	6	9	10	29	33	1	38	25	41	0	1	0	3	F	D	181	314	40
	865370773	11590	25920680	51963	46	20	6	9	10	29	33	1	38	25	41	0	1	0	3	F	D	181	314	40
	4	45790																						
12	865370503	8810	25920413	51560	29	20	7	20	15	35	36	1	30	19	21	0	1	0	3	F	D	200	317	41
	865370507	7870	25920420	51560	29	20	7	20	15	35	36	1	30	19	21	0	1	0	3	F	D	200	317	41
	865370512	8920	25920444	51469	50	20	7	10	11	25	42	1	32	19	21	0	1	0	3	F	D	178	313	42
	865370531	8940	25920451	51469	50	20	7	10	11	25	42	1	32	19	21	0	1	0	3	F	D	178	312	42
	865370541	9270	25920468	51469	50	20	7	10	11	25	42	1	32	19	21	0	1	0	3	F	D	177	313	42
	865371876	8920	26058249	51560	29	20	7	20	15	35	36	1	30	19	21	0	1	0	3	F	D	196	318	42
	6	52730																						
	10	98520																						

REMARKS

 TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.
 REFERENCES

 DCO1

GENT 07-06-2019

R. SLOCK
 QUALITY DEPARTMENT

 Z01

CO4 CONDITION OF THE SPECIMEN V: AGED F: NON-AGED N: NORMALISED	CO2 DIRECTION SPECIMEN L: OGR S: 45GR D: 9OGR
--	--