


A01  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België) Tel.: +32 9.347.31.11 Fax: +32 9.347.49.07	A02 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 221121123 P. 01/01	A09 DISPATCH NOTE 4150911 DATE 12-08-2022	A06.1 CUSTOMER HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0501838
	A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	A08 ORDER NUMBER 88288 DATE	A07 YOUR ORDER NO 15884 DATE 01-06-2022	A06.2 DESTINATION HTM YHTIOT OY TIILITEHTAANTIE 23 FIN-12310 RYTTYLAE FINLAND 0050183
		CONTRACT NO GC23HTMOO2	YOUR REFERENCES	
		OUR REFERENCES OBC-AU/DHAH		

BO1-BO4 SEE BELOW

BO9 ITEM	B10 WIDTH MM	B11 THICKNESS MM	REF. CUSTOMER
06	1.500	2.00	DCO1

CHEMICAL ANALYSIS																				MECHANICAL PROPERTIES				
C70 STEELMAKING PROCESS: LD																				TENSILE TEST				
BO9 ITEM	PACK NR	B13 GROSS WEIGHT KG	BO7 COIL NO	BO8 CAST N.	C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	CO4	CO2	C11 YIELD Rp0.2 MPa	C12 STRENGTH Rm MPa	C13 A %
					C	Mn	Si	P	S	N	Al _t	Ti	Cr	Ni	Cu	Nb	B	V	Mo					
06	867222062 1	9790 9790	55131359	94520	2	10	3	14	12	23	64	60	25	17	22	0	3	2	5	F	D	175	302	42
	1	9790																						

BO1-BO4

- MATERIAL - COLD ROLLED STEEL COILS, ANNEALED, SKINPASSED,
 (00-12-2006)
 QUALITY DCO1
 - STAND: EN 10131 (2006) NORM.TOL.
 REMARKS


STANDARD = EN 10130:2006

TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.
 REFERENCES

DCO1

GENT 12-08-2022

R. SLOCK
 QUALITY DEPARTMENT



Z01

CO4 CONDITION OF THE SPECIMEN V: AGED F: NON-AGED N: NORMALISED	CO2 DIRECTION SPECIMEN L: OGR S: 45GR D: 9OGR
--	--