

MÜ TER ADI & ADRES  
NAME & ADDRESS OF THE CUSTOMER  
FEON OY  
Teollisuuskatu 33, FI-00510 P.O. Bo FI-00511  
Helsinki, Finland  
F NLAND YA 358 40 801 0894

DESCRIPTION OF GOODS:  
ERW HOLLOW SECTIONS

**Ürün Bilgisi ve Mekanik Testler/Product Information and Mechanical Tests**

SIRA ITEM	TIP TYPE	EBAT SIZE	PAKET NO PACK NO	DÖKÜM CAST NO	PPB	LOT NO	URT.NORM PRODUCT NORM	KAL TE STEEL GRADE	YS N/mm <sup>2</sup>	TS N/mm <sup>2</sup>	E %	IE 1 J	IE 2 J	IE 3 J	IE AV. J	TT °C	HT BAR	HT TIME Sec	VDC	FT	BD	EX	NDE	B
218	CHS	76,10X3,00X12000	MB05595152	2203321	19	PO 41550	EN 10219	S355J2H	445	550	28.1									G	G		G	G
219	R	80X40X3,00X6000	MB05595513	2203622	66	PO 41550	EN 10219	S355J2H	449	577	28.3									G	G		G	G
220	R	80X40X3,00X6000	MB05595514	2203618	66	PO 41550	EN 10219	S355J2H	449	583	26.2									G	G		G	G
221	R	80X40X3,00X6000	MB05595522	2203618	66	PO 41550	EN 10219	S355J2H	449	583	26.2									G	G		G	G
222	R	80X40X3,00X6000	MB05595553	2203622	66	PO 41550	EN 10219	S355J2H	449	577	28.3									G	G		G	G
223	R	80X40X3,00X6000	MB05595558	2203622	66	PO 41550	EN 10219	S355J2H	449	577	28.3									G	G		G	G
224	R	80X40X3,00X6000	MB05595559	2203618	66	PO 41550	EN 10219	S355J2H	449	583	26.2									G	G		G	G

**Kimyasal Testler / Chemical Tests**

SIRA ITEM	DÖKÜM NO HEAT NO	C %	SI %	S %	MN %	P %	AL %	CR %	MO %	NI %	CU %	N %	TI %	V %	SN %	NB %	CEIIV %	CEPCM %	
218	2203321	0.1106	0.1756	0.0106	1.1280	0.0163	0.0306	0.0947	0.0240	0.1382	0.3870	0.0044	0.0010	0.0108	0.0250			0.3595	0.2044
219	2203622	0.1269	0.1875	0.0089	1.1360	0.0102	0.0220	0.0756	0.0191	0.0973	0.4057	0.0051	0.0010	0.0062	0.0197			0.3699	0.2230
220	2203618	0.1279	0.2105	0.0108	1.1940	0.0121	0.0292	0.1036	0.0353	0.1063	0.3467	0.0055	0.0016	0.0064	0.0202			0.3862	0.2264
221	2203618	0.1279	0.2105	0.0108	1.1940	0.0121	0.0292	0.1036	0.0353	0.1063	0.3467	0.0055	0.0016	0.0064	0.0202			0.3862	0.2264
222	2203622	0.1269	0.1875	0.0089	1.1360	0.0102	0.0220	0.0756	0.0191	0.0973	0.4057	0.0051	0.0010	0.0062	0.0197			0.3699	0.2230
223	2203622	0.1269	0.1875	0.0089	1.1360	0.0102	0.0220	0.0756	0.0191	0.0973	0.4057	0.0051	0.0010	0.0062	0.0197			0.3699	0.2230
224	2203618	0.1279	0.2105	0.0108	1.1940	0.0121	0.0292	0.1036	0.0353	0.1063	0.3467	0.0055	0.0016	0.0064	0.0202			0.3862	0.2264

G : yi/Good  
YS :Akma Muk./Yield Strength(N/mm<sup>2</sup>)  
TS :Çekme Muk./Tensile Strength(N/mm<sup>2</sup>)  
E :Uzama/Elongation (%)  
NDE:Tahribatsız Test/Non Destructive Examination  
B: Havsall/ Bevelled  
VDC: Görsel Kontrol/ Visual&Dimensional Check  
EX: Geni letme/ Expanding  
HT: Hidrostatik Test/ Hydrostatic Text(Bar)  
IE :Darbe Enerjisi/Impact Energy(Joule)  
TT :Test Sıcaklı / Test Temp.for Impact Testing(C)  
HT TIME: Saniye/ Second  
FT: Yassılma/ Flattanning  
BD: Bükme/Bending  
PPB:Paket içi adet/Pieces per bundle

CHS:INDUSTRIAL PIPE  
R:RECTANGULAR HOLLOW SECTION  
S:SQUARE HOLLOW SECTION

CE marklaması EN 10219 kapsamında üretilen ürünler (LP, TP, ZP hariç) için geçerlidir.  
CE marking applies to those products (except TP, LP, ZP) which produced in accordance with EN 10219.  
EN 10219-1 CE Kapsam/Scope:  
10x0.60 - 339.7x13.00 / 10x10x0.60 - 250x250x13.00 / 20x10x0.60 - 300x200x13.00

ONAY / APPROVED BY  
ERW Fabrikaları Kalite Müdürü / ERW Plants Quality Manager  
Bülent SÖNMEZ  
bulent.sonmez@toscelik.com.tr



**TOSÇELİK** Profil ve Sac  
Tosçelik Profil ve Sac Endüstrisi A.Ş.  
Organize Sanayi Bölgesi  
80950 TOPRAKKALE/OSMANIYE TÜRKİYE  
T +90 (328) 826 80 80 F +90 (328) 826 88 88  
Asım Gündüz V.D. : 086 001 3021