



客戶名稱 Customer	DAMSTAHL OY	客戶編號 Customer No.	FFI005	證明書編號 Certificate No.	160722C0011
產品名稱 Production	PRIME COLD ROLLED STAINLESS STEEL SHEET	商業發票號碼 Commercial Invoice No.	J16070041	證明書日期 Date of Issue	2016/07/21
規範名稱 Specification	EN 10028-7-2007	客戶採購案號 PO No.	204133	訂單編號 Order No.	EC16040413-1
鋼種 Steel Grade	1.4301/1.4307	提貨單編號 Weight No.	C16070301	P.I.號碼 P.I.No.	A10504213

項目 Item No.	爐號 Heat No.	產品規格 Product Description		化學成份(%) Chemical Composition										拉伸試驗 Tension Test			*01 降伏強度 1.0% °C/W.Q.	*02 熱處理 °C/W.Q.	箱號 C/No.	Coil No			
		尺寸 Dimension	數量 Quantity Pcs	重量 Weight Kgs	表面 Finish	保護 Protect	碳 C X10 <sup>-3</sup>	矽 Si X10 <sup>-2</sup>	錳 Mn X10 <sup>-2</sup>	磷 P X10 <sup>-3</sup>	硫 S X10 <sup>-3</sup>	銅 Cu X10 <sup>-2</sup>	鎳 Ni X10 <sup>-2</sup>	鉻 Cr X10 <sup>-2</sup>	氮 N X10 <sup>-3</sup>	降伏 0.2%Y.S. MPa					抗拉 T.S. MPa	伸長率 E.L. %	
		Specification		Min.	Max.																		
1	C34BP1500335	1.5mm x1,500.0mm x3,000.0mm	19	1,004	NO.4	FLPE	21	44	145	30	45	15	1050	1950	100	100	700	540	45	250	1000	20	QEY1514
2	C34BP1500335	1.5mm x1,500.0mm x3,000.0mm	19	1,005	NO.4	FLPE	21	44	145	30	7	803	1817	44	283	638	638	53	339	1050	21	QEY1514	
3	C34BP1500335	1.5mm x1,500.0mm x3,000.0mm	18	952	NO.4	FLPE	21	44	145	30	7	803	1817	44	283	638	638	53	339	1050	22	QEY1514	
4	C34BP1500335	1.5mm x1,500.0mm x3,000.0mm	18	951	NO.4	FLPE	21	44	145	30	7	803	1817	44	283	638	638	53	339	1050	23	QEY1514	
5	C34BP1600300	2mm x1,250.0mm x2,500.0mm	20	976	NO.4	FLPE	21	39	145	29	3	804	1811	42	262	639	639	56	314	1050	24	QFD0065	
6	C34BP1600300	2mm x1,250.0mm x2,500.0mm	20	977	NO.4	FLPE	21	39	145	29	3	804	1811	42	262	639	639	56	314	1050	25	QFD0065	
7	C34BP1600300	2mm x1,250.0mm x2,500.0mm	20	978	NO.4	FLPE	21	39	145	29	3	804	1811	42	262	639	639	56	314	1050	26	QFD0065	
8	C34BP1500199	2mm x1,500.0mm x3,000.0mm	20	983	NO.4	FLPE	15	38	143	31	3	805	1819	40	298	655	655	51	343	1050	27	QEX1231	
9	C34BP1500199	2mm x1,500.0mm x3,000.0mm	14	984	NO.4	FLPE	15	38	143	31	3	805	1819	40	298	655	655	51	343	1050	28	QEX1231	
10	C34BP1500199	2mm x1,500.0mm x3,000.0mm	14	983	NO.4	FLPE	15	38	143	31	3	805	1819	40	298	655	655	51	343	1050	29	QEX1231	
11	C34BP1500199	2mm x1,500.0mm x3,000.0mm	14	982	NO.4	FLPE	15	38	143	31	3	805	1819	40	298	655	655	51	343	1050	30	QEX1231	
12	C34BP1500199	2mm x1,500.0mm x3,000.0mm	14	983	NO.4	FLPE	15	38	143	31	3	805	1819	40	298	655	655	51	343	1050	31	QEX1231	
13	C34BP1500199	2mm x1,500.0mm x3,000.0mm	10	1,053	NO.4	FLPE	18	47	143	31	5	804	1826	39	280	632	632	53	327	1050	32	QEX1231	
14	C34BP1600090	3mm x1,500.0mm x3,000.0mm	10	1,053	NO.4	FLPE	18	47	143	31	5	804	1826	39	280	632	632	53	327	1050	33	QEY1206	
15	C34BP1600090	3mm x1,500.0mm x3,000.0mm	9	948	NO.4	FLPE	18	47	143	31	5	804	1826	39	280	632	632	53	327	1050	34	QEY1206	
16	C34BP1600090	3mm x1,500.0mm x3,000.0mm	9	948	NO.4	FLPE	18	47	143	31	5	804	1826	39	280	632	632	53	327	1050	35	QEY1206	
17	C34BP1600090	3mm x1,500.0mm x3,000.0mm	11	1,156	NO.4	FLPE	18	47	143	31	5	804	1826	39	280	632	632	53	327	1050	36	QEY1206	
18	C34BP1600090	3mm x1,500.0mm x3,000.0mm	13	951	NO.4	FLPE	18	47	143	31	4	802	1818	43	276	635	635	51	315	1050	37	QEY1206	
19	C34BP1600384	3mm x1,250.0mm x2,500.0mm	286	18,844	NO.4	FLPE	21	38	143	29	4	802	1818	43	276	635	635	51	315	1050	39	QFE1055	
		TOTAL:																					

附註 Remark  
1. Standards: ASTM A240/A480  
2. THE GRADE COMPLIES TO EN10088-4  
Alloy Verification(PMI) : OK  
Intergranular Corrosion Test (according to EN ISO 3651-2 Method A) : OK  
This certificate complies to 3.1/EN 10204:2004.  
The material grade according to EN 10088-2、EN 10088-4、EN 10028-7  
Visual Inspection(Surface) and Dimension Check : OK  
1.MPa=1N/mm<sup>2</sup>=10bar=145psi=  
10.2kgf/cm<sup>2</sup>

Surveyor By	N/A	1.ISO 9001:2008 (No.01 100 056299) 2.PED / AD2000 (No.01 202 TWM/Q-05 0105) 3.ISO 14001:2004 (No.01 104 822 096385) 4.OHSAS 18001:2007 (No.01 113 822 096385)	Manager of Quality Assurance Department  How Yu Shih
-------------	-----	--	--