

Business Unit / QCM

Avesta Works / Jerker Sterneland

Date Datum Date

12-May-2021



Load, Ladung, Charge No

FI/223650

Acknowledged ID, Bestätigung, Commande ID

6610/300600574

Your ref, Ihre Ref., Votre ref 14630.		Requirements, Anforderungen, Exigences ASTM A240/A240M-20a ASME BPVC SEC II PART A SA-240/SA-240M Ed 2019 EN 10088-2:2014 EN 10028-7:2016 AD 2000 W2, W10 & EN 10028-7 NACE MR0175 / ISO 15156-3:2015 EN ISO 9444-2 / ASTM A480M	
Buyer, Besteller, Acheteur HTM Yhtiöt Oy Tiilitehtaantie 23 FI 12310, RYTTYLÄ FINLAND			
Consignee, Empfänger, Lieu de livraison HTM Yhtiöt Oy			

Mark of Manufacturer Zeichen des Lieferwerkes Signe de producteur 	Process Erschmelzungsart Mode de fusion E+AOD	Inspector's stamp Zeichen des Sachverständigen Poicon de l'expert 	Grade, Werkstoff, Nuance Outokumpu Supra 316L/4404 TYPE 316 TYPE 316L 1.4401 1.4404
--	---	--	---

Product, Erzeugnisform, Produit
Stainless Steel Hot Rolled, Coil-Plate
finish 1D, cut edge

Line Reihe Ligne	Item Position Poste	Heat-Lot No Schmelze-Lot Nr Coulée n° - Lot No	Size Abmessungen Dimensions	Pieces Stückzahl Nombre	Quantity / Unit Menge / Einheit Quantité / Unité
1	5	30666-001	10,00 X 1500 X 3000 mm	14	5011 KG

Chemical composition – Chemische Zusammensetzung – Composition chimiques

	C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Nb	Cu	Co	N
Heat	.023	.49	.91	.036	.002	17.09	10.00	2.06	.005	.022	.48	.19	.031

Radioactive contamination check acc. IAEA recommendations: **Approved**

Test results – Prüfergebnisse – Results desais (1N/mm² = 1 MPa) F = Front – Anfan – Debut B = Back – Ende – Fin T = Transverse – Quer – Travers

Test Ref	Temp °C	RP 0.2 N/MM2	RP 1.0 N/MM2	RM N/MM2	A5 %	2" %	HB
Min	+20	240	270	530	40	40	HB
Max				680			217
F T	+20	315	349	585	59	61	192
B T		311	345	581	60	62	183

Certified acc. to AD 2000-Merkblatt W0 by TÜV NORD, notified body, Reg-No. 0045
Material conforms to NACE MR0175 / ISO 15156-3 in supplied condition
Corrosion acc. ASTM A 262-E, EN ISO 3651-2A: Approved
Heat treatment / Solution annealed: Material temp minimum 1040 °C / Quenched (forced air + water)
Steel grade verification (PMI-spectroscopic): Approved
Marking, visual insp. and gauge measurement: Approved
Certified acc. to PED 2014/68/EU by TÜV NORD, notified body, Reg-No. 0045