

Business Unit / QCM

Avesta Works / Jerker Sterneland

Date Datum Date

20-May-2021



Load, Ladung, Charge No

FI/224032

Acknowledged ID, Bestätigung, Commande ID

6610/300601573

Your ref, Ihre Ref., Votre ref 018717-1		Requirements, Anforderungen, Exigences <b>ASTM A240/A240M-20a</b> <b>ASME BPVC SEC II PART A SA-240/SA-240M Ed 2019</b> <b>EN 10088-2:2014</b> <b>EN 10028-7:2016</b> <b>AD 2000 W2, W10 &amp; EN 10028-7</b> <b>NACE MR0175 / ISO 15156-3:2015</b> <b>EN ISO 9444-2 / ASTM A480M</b>	
Buyer, Besteller, Acheteur Ovako Metals Oy Ab ATOMITIE 5 A FI 00370, HELSINKI FINLAND			
Consignee, Empfänger, Lieu de livraison Ovako Metals Oy Ab			

Mark of Manufacturer Zeichen des Lieferwerkes Signe de producteur 	Process Erschmelzungsart Mode de fusion <b>E+AOD</b>	Inspector's stamp Zeichen des Sachverständigen Poicon de l'expert 	Grade, Werkstoff, Nuance Outokumpu Supra 316L/4404 TYPE 316 TYPE 316L 1.4401 1.4404
--	---	--	--

Product, Erzeugnisform, Produit  
**Stainless Steel Hot Rolled, Coil-Plate**  
**finish 1D, cut edge**

Line Reihe Ligne	Item Position Poste	Heat-Lot No Schmelze-Lot Nr Coulée n° - Lot No	Size Abmessungen Dimensions	Pieces Stückzahl Nombre	Quantity / Unit Menge / Einheit Quantité / Unité
1	1	30854-003	10,00 X 1500 X 3000 mm	8	2879 KG

Chemical composition – Chemische Zusammensetzung – Composition chimiques

	C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Nb	Cu	Co	N
Heat	.020	.48	.77	.034	.001	17.02	10.02	2.03	.005	.012	.39	.20	.036

Radioactive contamination check acc. IAEA recommendations: **Approved**

Test results – Prüfergebnisse – Results dessais (1N/mm<sup>2</sup> = 1 MPa) F = Front – Anfan – Debut B = Back – Ende – Fin T = Transverse – Quer – Travers

Test Ref	Temp °C	RP 0.2 N/MM2	RP 1.0 N/MM2	RM N/MM2	A5 %	2" %	HB
Min	+20	240	270	530	40	40	HB
Max				680			217
F T	+20	325	361	599	58	60	183
B T		325	362	598	59	61	178

**Certified acc. to AD 2000-Merkblatt W0 by TÜV NORD, notified body, Reg-No. 0045**  
**Material conforms to NACE MR0175 / ISO 15156-3 in supplied condition**  
**Corrosion acc. ASTM A 262-E, EN ISO 3651-2A: Approved**  
**Heat treatment / Solution annealed: Material temp minimum 1040 °C / Quenched (forced air + water)**  
**Steel grade verification (PMI-spectroscopic): Approved**  
**Marking, visual insp. and gauge measurement: Approved**  
**Certified acc. to PED 2014/68/EU by TÜV NORD, notified body, Reg-No. 0045**