

Delivery address, Empfänger, Lieu de livraison TIBNOR OY					TIBNOR OY						
TUOTEKATU 3 33840 TAMPERE SUOMI - FINLAND					ATOMITIE 5 A 00370 HELSINKI SUOMI - FINLAND						
Requirements, Anforderungen, Exigences EN 10088-4:2009 AD 2000 W2, W10 & EN 10028-7:2007 ASTM A240/A240M ASME SA-240/SA-240M II A ED. 2013					Our Order No. Unser Auftrag Nr. Notre commande n° 300304374		Your order, Ihre Bestellung, Votre commande 45961941-0710				
Product, Erzeugnisform, Produit SHEET , STAINLESS STEEL					Mark of Manufacturer Zeichen des Lieferwerkes Signe de producteur outokumpu		Process Erschmelzungsart Mode de fusion AOD		Inspector's stamp Zeichen d. Sachverst. Poicon de l'expert 		
Grade, Werkstoff, Nuance 1.4404 TYPE 316L 1.4401					Tolerances Toleranzen, Tolérances EN ISO 9445-2						
Marking, Kennzeichnung, Marquage 1.4404 2B					Marks, Versandzeichen, Marques						
Line Reihe Ligne	Item Position Poste	Charge-test No. Schmelze-Probe Nr. Coulée n°	Size, Abmessungen, Dimensions			Quantity Stückzahl Nombre	Weight, Gewicht, Poids	Finish Ausführung Fini EN/ASTM	 14 0045-CPR-0567		
1	16	39008 5	5,0 X 1500 X 3000 MM			18	3214 KG	2B			
Charge no. Schmelze Nr. Coulée n°	Chemical composition, Chemische Zusammensetzung, Composition chimiques										
	C %	Si %	Mn %	P %	S %	Cr %	Ni %	MO %	N %		
	0,019	0,48	0,87	0,032	<.001	16,6	10,0	2,02	0,042		
Line Reihe Ligne	Mechanical properties, Mechanische Eigenschaften, Caracteristiques mecaniques								Tensile test, Zugversuch, Essai de traction		
	Location Ort Lieu	Rp0.2 MPa	Rp1.0 MPa	Rm MPa	A5 %	A50 %	%	Hardness Härte, Duraté HBW	ISO 6892-1:2009 A224 SAMPLES PERPENDICULAR TO THE ROLLING DIRECTION APPROVED ACC.TO AD2000-WO WITH VERIFICATION OF THE UNIFORMITY OVER THE STRIP LENGTH. CERTIFIED ACC. TO PED 97/23/EC BY TÜV NORD REG. NO. 0045. DOPS ACC. TO CPR AVAILABLE ON THE WEB PAGE BY STEEL NUMBER		
1	E	318	355	591	54	52		174			
	A	315	347	595	54	53		173			
Identity test, Verwechslungsprüfung, Controle d'identification Sizes, Abmessungen, Dimensions Surface, Oberfläche, Surface Test of intergran. corros, Prüfung auf interkrist. Korros, Test de corros. intercrst. EN ISO 3651-2 A: OK					OK		OK		A = Beginning / Anfang / Début E = End / Ende / Fin		
ASTM A240/A240M ASME SA-240/SA-240M II A ED. 2013 TYPE 316 NACE MR0103-2012 AND NACE MR0175/ISO 15156-1 / NACE MR0175/ISO 15156-3 186277					We certify that the above mentioned products comply with the terms of the order contract. Wir bestätigen, dass die Lieferung den Vereinbarungen der Bestellannahme entspricht. Nous certifions que les produits énumérés ci-dessus sont conformes aux prescriptions de la commande.					This test certificate is made by controlled ADP-system and is valid without signature. Dieses Zeugnis wurde von einem überprüften Datenverarbeitungssystem erstellt und ist ohne Unterschrift gültig. Ce certificat a été établi par un système informatique contrôlé et est valide sans signature.	
					Outokumpu Stainless Oy						
					Authorized inspector Werkssachverständiger Inspecteur autorisé MINNA TAIVAINEN						
					FI-95490 Tornio, Finland Tel. +358 16 4521, Fax +358 16 452 350, www.outokumpu.com Domicile: Tornio, Finland. Business Identity Code 0823315-9						