

Delivery address, Empfänger, Lieu de livraison BE GROUP OY AB LOTILA KIRKKAAT 2, OVET 5-7 VANHANRADANKATU 42 15522 LAHTI SUOMI-FINLAND				BE GROUP OY AB HELSINGINTIE 50 15100 LAHTI SUOMI-FINLAND								
Requirements, Anforderungen, Exigences EN 10088-4:2009 AD 2000 W2, W10 & EN 10028-7:2007 ASTM A240/A240M ASME SA-240/SA-240M II A ED. 2013				Our Order No. Unser Auftrag Nr. Notre commande n° 300332932	Your order, Ihre Bestellung, Votre commande P031663							
Product, Erzeugnisform, Produit SHEET , STAINLESS STEEL				Mark of Manufacturer Zeichen des Lieferwerkes Signe de producteur outokumpu	Process Erschmelzungsart Mode de fusion AOD	Inspector's stamp Zeichen d. Sachverst. Poicon de l'expert 						
Grade, Werkstoff, Nuance 1.4307 1.4301 TYPE 304				Tolerances Toleranzen, Tolérances EN ISO 9445-2								
Marking, Kennzeichnung, Marquage 1.4307 2B				Marks, Versandzeichen, Marques								
Line Reihe Ligne	Item Position Poste	Charge-fast Nn Schmelze-Probe Nr. Coulée n°	Size, Abmessungen, Dimensions		Quantity Stückzahl Nombre	Weight, Gewicht, Poids	Finish Ausführung Fini EN/ASTM					
1	3	47940 1	4,0 X 1000 X 2000 MM		17	1066 KG	2B					
2	5	39353 1	5,0 X 1500 X 3000 MM		28	4940 KG	2B					
 14 0045-CPR-0567												
Charge no. Schmelze Nr. Coulée n°	Chemical composition, Chemische Zusammensetzung, Composition chimiques											
	C %	Si %	Mn %	P %	S %	Cr %	Ni %	N %				
47940	0,019	0,54	1,47	0,032	<.001	18,1	8,0	0,049				
39353	0,023	0,38	1,52	0,028	0,004	18,1	8,0	0,040				
Line Reihe Ligne	Mechanical properties, Mechanische Eigenschaften, Caracteristiques mecaniques								Tensile test, Zugversuch, Essai de traction			
	Location Ort Lieu	Rp0.2 MPa	Rp1.0 MPa	Rm MPa	A5 %	A50 %	%	Hardness Härte, Duraté HBW	ISO 6892-1:2009 A224 SAMPLES PERPENDICULAR TO THE ROLLING DIRECTION			
1	E	330	363	627	54	52		191	APPROVED ACC.TO AD2000-WO WITH VERIFICATION OF THE UNIFORMITY OVER THE STRIP LENGTH. CERTIFIED ACC. TO PED 97/23/EC BY TUV NORD REG. NO. 0045. DOPS ACC. TO CPR AVAILABLE ON THE WEB PAGE BY STEEL NUMBER			
	A							180				
2	E	301	332	624	53	52		187				
	A	293	325	625	54	53		185				
Identity test, Verwechslungsprüfung, Controle d'identification Gizes, Abmessungen, Dimensions Surface, Oberfläche, Surface Test of intergran. corros, Prüfung auf interkrist. Korros, Test de corros. intercrst.				EN ISO 3651-2 A: OK				OK OK OK	A = Beginning / Anfang / Début E = End / Ende / Fin			
ASTM A240/A240M ASME SA-240/SA-240M II A ED. 2013 TYPE 304L NACE MR0103-2012 AND NACE MR0175/ISO 15156-1 / NACE MR0175/ISO 15156-3 3101103170 3101104605				We certify that the above mentioned products comply with the terms of the order contract. Wir bestätigen, dass die Lieferung den Vereinbarungen der Bestellannahme entspricht. Nous certifions que les produits énumérés ci-dessus sont conformes aux prescriptions de la commande.				This test certificate is made by controlled ADP-system and is valid without signature. Dieses Zeugnis wurde von einem überprüften Datenverarbeitungssystem erstellt und ist ohne Unterschrift gültig. Ce certificat a été établi par un système informatique contrôlé et est valide sans signature.				
				Outokumpu Stainless Oy <i>Anne-Maria Salmi</i>								
				Authorized Inspector Werkssachverständiger Inspecteur autorisé ANNE-MARIA SALMI								
				FI-95490 Tornio, Finland Tel. +358 16 4521, Fax +358 16 452 350, www.outokumpu.com Domicile: Tornio, Finland. Business Identity Code 0823315-9								