



Business Unit / QCM Avesta Works / Jerker Sterneland Date Datum Date 01-Oct-2019 Load, Ladung, Charge No FI/194307 Acknowledged ID, Bestätigung, Commande ID 6610/300530991

Your ref, Ihre Ref., Votre ref 012483-1		Requirements, Anforderungen, Exigences <b>ASTM A 240M-18</b> <b>ASME BPVC SEC II PART A SA-240/SA-240M Ed 2019</b> <b>EN 10088-2:2014</b> <b>EN 10028-7:2016</b> <b>AD 2000 W2, W10 &amp; EN 10028-7</b> <b>NACE MR0175 / ISO 15156-3:2015</b> <b>EN ISO 9444-2 / ASTM A480M</b>	
Buyer, Besteller, Acheteur Ovako Metals Oy Ab ATOMITIE 5 A FI 00370, HELSINKI FINLAND			
Consignee, Empfänger, Lieu de livraison Ovako Metals Oy Ab			

Mark of Manufacturer Zeichen des Lieferwerkes Signe de producteur <b>outokumpu</b>	Process Erschmelzungsart Mode de fusion <b>E+AOD</b>	Inspector's stamp Zeichen des Sachverständigen Poicon de l'expert 	Grade, Werkstoff, Nuance <b>Outokumpu Core 304L/4307</b> <b>TYPE 304</b> <b>TYPE 304L</b> <b>1.4301</b> <b>1.4307</b>
---	---	---	--

Product, Erzeugnisform, Produit  
**Stainless Steel Hot Rolled, Coil-Plate**  
**finish 1D, cut edge**

Line Reihe Ligne	Item Position Poste	Heat-Lot No Schmelze-Lot Nr Coulée n° - Lot No	Size Abmessungen Dimensions	Pieces Stückzahl Nombre	Quantity / Unit Menge / Einheit Quantité / Unité
1	3	E191178-785	10,00 X 1500 X 3000 mm	29	10366 KG

Chemical composition – Chemische Zusammensetzung – Composition chimiques

	C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Nb	Cu	Co	N
Heat	.019	.32	1.38	.036	.001	18.43	8.08	.54	.003	.024	.56	.23	.070

Radioactive contamination check acc. IAEA recommendations: **Approved**

Test results – Prüfergebnisse – Results dessais (1N/mm² = 1 MPa) F = Front – Anfan – Debut B = Back – Ende – Fin T = Transverse – Quer – Travers

Test Ref	Temp	RP 0.2	RP 1.0	RM	A5	2"	HB
	°C	N/MM2	N/MM2	N/MM2	%	%	HB
Min	+20	230	260	520	45	40	
Max				700			201
F T	+20	321	365	627	55	57	187
B T		322	364	620	57	59	187

**Certified acc. to AD 2000-Merkblatt W0 by TÜV NORD, notified body, Reg-No. 0045**  
**Material conforms to NACE MR0175 / ISO 15156-3 in supplied condition**  
**Corrosion acc. ASTM A 262-E, EN ISO 3651-2A: Approved**  
**Heat treatment / Solution annealed: Material temp minimum 1040 °C / Quenched (forced air + water)**  
**Steel grade verification (PMI-spectroscopic): Approved**  
**Marking, visual insp. and gauge measurement: Approved**  
**Certified acc. to PED 2014/68/EU by TÜV NORD, notified body, Reg-No. 0045**